

Stanyl® TS341-N

PA46

Properties	Typical Data	Unit	Test Method
Rheological properties			
	dry / cond		
Molding shrinkage [parallel]	2 / *	%	Sim. to ISO 294-4
Molding shrinkage [normal]	2 / *	%	Sim. to ISO 294-4
Mechanical properties			
	dry / cond		
Tensile modulus	3300 / 1000	MPa	ISO 527-1/-2
Tensile modulus (120°C)	800 / -	MPa	ISO 527-1/-2
Tensile modulus (160°C)	650	MPa	ISO 527-1/-2
Tensile modulus (180°C)	600	MPa	ISO 527-1/-2
Tensile modulus (200°C)	500	MPa	ISO 527-1/-2
Yield stress	100 / 55	MPa	ISO 527-1/-2
Yield stress (120°C)	50	MPa	ISO 527-1/-2
Yield stress (160°C)	40	MPa	ISO 527-1/-2
Yield stress (180°C)	35	MPa	ISO 527-1/-2
Yield stress (200°C)	30	MPa	ISO 527-1/-2
Nominal strain at break	40 / >50	%	ISO 527-1/-2
Nominal strain at break (120°C)	>50	%	ISO 527-1/-2
Nominal strain at break (160°C)	>50	%	ISO 527-1/-2
Nominal strain at break (180°C)	>50	%	ISO 527-1/-2
Nominal strain at break (200°C)	>50	%	ISO 527-1/-2
Flexural modulus	3000 / 900	MPa	ISO 178
Flexural modulus (120°C)	800	MPa	ISO 178
Flexural modulus (160°C)	600	MPa	ISO 178
Charpy impact strength (+23°C)	N / N	kJ/m ²	ISO 179/1eU



Stanyl[®] TS341-N

Properties	Typical Data	Unit	Test Method
Charpy impact strength (-30°C)	N / N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	10 / 35	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	4 / 4	kJ/m ²	ISO 179/1eA
Izod notched impact strength (+23°C)	10 / 35	kJ/m ²	ISO 180/1A
Izod notched impact strength (-40°C)	4 / 4	kJ/m ²	ISO 180/1A

Thermal properties

dry / cond

Melting temperature (10°C/min)	295 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	190 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	280 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.85 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	1.1 / *	E-4/°C	ISO 11359-1/-2

Electrical properties

dry / cond

Volume resistivity	1E13 / 1E10	Ohm*m	IEC 60093
Electric strength	25 / 20	kV/mm	IEC 60243-1
Relative permittivity (100Hz)	4 / 13	-	IEC 60250
Relative permittivity (1 MHz)	3.6 / 4.3	-	IEC 60250

Other properties

dry / cond

Humidity absorption	3.7 / *	%	Sim. to ISO 62
Density	1180 / -	kg/m ³	ISO 1183

