

Akulon® S227-C

PA66


Unreinforced, Medium Viscosity, Lubricated, Food Contact Quality, Extrusion Grade

Properties	Typical Data	Unit	Test Method
Material specific properties			
	dry / cond		
Viscosity number	180 / *	cm ³ /g	ISO 307, 1157, 1628
RSV formic acid, 1g/100ml	2.75	-	DSM method
Density	1140 / -	kg/m ³	ISO 1183
Thermal properties			
	dry / cond		
Coeff. of linear therm. expansion (parallel)	0.9 / *	E-4/°C	ISO 11359-1/-2



Akulon[®] S227-C

Viscosity-shear rate



Rheology calculator 2019

