

DSM Engineering Plastics - Property Data

Akulon® S223-P2

(PA66+Imod)-unfilled

Properties	Typical Data	Unit	Test Method
MECHANICAL PROPERTIES		dry / cond	
Tensile modulus	2700 / -	MPa	ISO 527-1/-2
Yield stress	70 / -	MPa	ISO 527-1/-2
Yield strain	4 / -	%	ISO 527-1/-2
Nominal strain at break	30 / -	%	ISO 527-1/-2
Charpy impact strength (+23°C)	N / N	kJ/m ²	ISO 179/1eU
Charpy impact strength (-30°C)	N / N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	40 / 55	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	15 / 15	kJ/m ²	ISO 179/1eA
THERMAL PROPERTIES		dry / cond	
Melting temperature (10°C/min)	260 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	70 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	210 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	1.2 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	1.2 / *	E-4/°C	ISO 11359-1/-2
Burning Behav. at 1.6 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.6 / *	mm	IEC 60695-11-10
ELECTRICAL PROPERTIES		dry / cond	
Relative permittivity (100Hz)	3.1 / 10	-	IEC 60250
Relative permittivity (1 MHz)	2.7 / 4	-	IEC 60250
Dissipation factor (100 Hz)	90 / 14000	E-4	IEC 60250
Dissipation factor (1 MHz)	150 / 1000	E-4	IEC 60250
Volume resistivity	1E13 / 1E10	Ohm*m	IEC 60093
Surface resistivity	* / 1E14	Ohm	IEC 60093
Electric strength	25 / 20	kV/mm	IEC 60243-1
Comparative tracking index	600 / 600	-	IEC 60112
OTHER PROPERTIES		dry / cond	
Water absorption	7.9 / *	%	Sim. to ISO 62
Humidity absorption	2.2 / *	%	Sim. to ISO 62
Density	1200 / -	kg/m ³	ISO 1183

DSM Product

Unlimited. **DSM**

