

Akulon® S222

PA66

Low Viscosity

Properties	Typical Data	Unit	Test Method
Mechanical properties	dry / cond		
Tensile modulus	3600 / 1500	MPa	ISO 527-1/-2
Nominal strain at break	10 / >50	%	ISO 527-1/-2
Yield stress	95 / 60	MPa	ISO 527-1/-2
Yield strain	3.5 / 20	%	ISO 527-1/-2
Flexural modulus	2800 / -	MPa	ISO 178
Flexural strength	125 / -	MPa	ISO 178
Charpy notched impact strength (+23°C)	6 / 12	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	6 / 6	kJ/m ²	ISO 179/1eA
Thermal properties	dry / cond		
Melting temperature (10°C/min)	260 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	85 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	215 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	1 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	1 / *	E-4/°C	ISO 11359-1/-2
Other properties	dry / cond		
Water absorption	8.5 / *	%	Sim. to ISO 62
Humidity absorption	2.3 / *	%	Sim. to ISO 62
Density	1140 / -	kg/m ³	ISO 1183
Material specific properties	dry / cond		
Viscosity number	130 / *	cm ³ /g	ISO 307, 1157, 1628

