

Novamid® 3021G10 NA99001

PA66-GF10

Properties	Typical Data	Unit	Test Method
Mechanical properties			
	dry / cond		
Tensile modulus	5500 / -	MPa	ISO 527-1/-2
Stress at break	110 / -	MPa	ISO 527-1/-2
Strain at break	2.5 / -	%	ISO 527-1/-2
Charpy impact strength (+23°C)	30 / -	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	4 / -	kJ/m ²	ISO 179/1eA
Other properties			
	dry / cond		
Density	1200 / -	kg/m ³	ISO 1183

