

Arnite® B436 SE

PBT-GF30 FR(17)

30% Glass Reinforced, Flame Retardant

Properties	Typical Data	Unit	Test Method
Mechanical properties			
	Value		
Tensile modulus	10500	MPa	ISO 527-1/-2
Stress at break	105	MPa	ISO 527-1/-2
Strain at break	1.7	%	ISO 527-1/-2
Charpy impact strength (+23°C)	45	kJ/m ²	ISO 179/1eU
Charpy impact strength (-30°C)	45	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	6	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	6	kJ/m ²	ISO 179/1eA
Thermal properties			
	Value		
Melting temperature (10°C/min)	225	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	210	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	220	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.35	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.7	E-4/°C	ISO 11359-1/-2
Glow Wire Flammability Index GWFI	960	°C	IEC 60695-2-12
GWFI (Thickness (1) tested)	1.5	mm	IEC 60695-2-12
Electrical properties			
	Value		
Relative permittivity (100Hz)	4.1	-	IEC 62631-2-1
Relative permittivity (1 MHz)	3.9	-	IEC 62631-2-1
Dissipation factor (100 Hz)	20	E-4	IEC 62631-2-1
Dissipation factor (1 MHz)	150	E-4	IEC 62631-2-1
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1



Property Data

Arnite[®] B436 SE

Properties	Typical Data	Unit	Test Method
Electric strength	28	kV/mm	IEC 60243-1
Comparative tracking index	250	V	IEC 60112

Other properties	Value		
Water absorption	0.3	%	Sim. to ISO 62
Humidity absorption	0.15	%	Sim. to ISO 62
Density	1670	kg/m ³	ISO 1183

