

Arnite® B437 SE/R

PBT-GF35 FR(17)

35% Glass Reinforced, Flame Retardant

Properties	Typical Data	Unit	Test Method
Mechanical properties			
	Value		
Tensile modulus	11500	MPa	ISO 527-1/-2
Stress at break	115	MPa	ISO 527-1/-2
Strain at break	1.5	%	ISO 527-1/-2
Charpy impact strength (+23°C)	40	kJ/m ²	ISO 179/1eU
Charpy impact strength (-30°C)	40	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	5	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	5	kJ/m ²	ISO 179/1eA
Thermal properties			
	Value		
Melting temperature (10°C/min)	225	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	210	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	220	°C	ISO 75-1/-2
Burning Behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.5	mm	IEC 60695-11-10
Glow Wire Flammability Index GWFI	960	°C	IEC 60695-2-12
GWFI (Thickness (1) tested)	1.5	mm	IEC 60695-2-12
Electrical properties			
	Value		
Relative permittivity (100Hz)	4.1	-	IEC 60250
Relative permittivity (1 MHz)	3.9	-	IEC 60250
Dissipation factor (100 Hz)	20	E-4	IEC 60250
Dissipation factor (1 MHz)	150	E-4	IEC 60250
Volume resistivity	>1E13	Ohm*m	IEC 60093



Property Data

Arnite[®] B437 SE/R

Properties	Typical Data	Unit	Test Method
Electric strength	28	kV/mm	IEC 60243-1
Comparative tracking index	250	V	IEC 60112
Other properties		Value	
Water absorption	0.3	%	Sim. to ISO 62
Humidity absorption	0.15	%	Sim. to ISO 62
Density	1690	kg/m ³	ISO 1183

