

DSM Engineering Plastics - Property Data


Arnite® T04 202

PBT-unfilled

Low Viscosity, Extrusion

Properties	Typical Data	Unit	Test Method
THERMAL PROPERTIES			
Melting temperature (10°C/min)	225	°C	ISO 11357-1/-3
OTHER PROPERTIES			
Water absorption	0.45	%	Sim. to ISO 62
Humidity absorption	0.18	%	Sim. to ISO 62
Density	1300	kg/m³	ISO 1183
MATERIAL SPECIFIC PROPERTIES			
RSV m-cresol, 1g/100ml	1.85	-	DSM method

VISCOSITY-SHEAR RATE



DSM Product

Unlimited. **DSM**

