

# DSM Engineering Plastics - Property Data

## Xantar® MX 1000

PC-unfilled

Impact Modified, Flame Retardant, High Flow

| Properties                                   | Typical Data | Unit                   | Test Method     |
|----------------------------------------------|--------------|------------------------|-----------------|
| <b>RHEOLOGICAL PROPERTIES</b>                |              |                        |                 |
| Melt volume-flow rate                        | 30           | cm <sup>3</sup> /10min | ISO 1133        |
| Temperature                                  | 300          | °C                     | ISO 1133        |
| Load                                         | 1.2          | kg                     | ISO 1133        |
| Molding shrinkage (parallel)                 | 0.6          | %                      | ISO 294-4       |
| <b>MECHANICAL PROPERTIES</b>                 |              |                        |                 |
| Tensile modulus                              | 2200         | MPa                    | ISO 527-1/-2    |
| Yield stress                                 | 55           | MPa                    | ISO 527-1/-2    |
| Yield strain                                 | 6            | %                      | ISO 527-1/-2    |
| Nominal strain at break                      | >50          | %                      | ISO 527-1/-2    |
| Flexural modulus                             | 2300         | MPa                    | ISO 178         |
| Flexural strength                            | 80           | MPa                    | ISO 178         |
| Izod notched impact strength (23°C)          | 40           | kJ/m <sup>2</sup>      | ISO 180/4A      |
| Rockwell hardness, M scale                   | 70           | -                      | ISO 2039-2      |
| <b>THERMAL PROPERTIES</b>                    |              |                        |                 |
| Temp. of deflection under load (1.80 MPa)    | 115          | °C                     | ISO 75-1/-2     |
| Vicat softening temperature (50°C/h 50N)     | 135          | °C                     | ISO 306         |
| Coeff. of linear therm. expansion (parallel) | 0.65         | E-4/°C                 | ISO 11359-1/-2  |
| Burning Behav. at 1.6 mm nom. thickn.        | V-0          | class                  | IEC 60695-11-10 |
| Thickness tested                             | 1.5          | mm                     | IEC 60695-11-10 |
| Burning Behav. at thickness h                | V-0          | class                  | IEC 60695-11-10 |
| Thickness tested                             | 3            | mm                     | IEC 60695-11-10 |
| Burning Behav. 5V at thickness h             | 5VB          | class                  | IEC 60695-11-20 |
| Thickness tested                             | 2            | mm                     | IEC 60695-11-20 |
| Oxygen index                                 | 33           | %                      | ISO 4589-1/-2   |
| Ball pressure temperature                    | 125          | °C                     | IEC 60695-10-2  |
| Glow Wire Flammability Index GWFI            | 960          | °C                     | IEC 60695-2-12  |
| GWFI (Thickness (1) tested)                  | 1.5          | mm                     | IEC 60695-2-12  |
| Glow Wire Flammability Index GWFI            | 960          | °C                     | IEC 60695-2-12  |
| GWFI (Thickness (2) tested)                  | 3            | mm                     | IEC 60695-2-12  |
| Relative Temperature Index - electrical      | 110          | °C                     | UL746B          |
| RTI electrical (Thickness (1) tested)        | 1.5          | mm                     | UL746B          |
| Relative Temperature Index - electrical      | 110          | °C                     | UL746B          |
| RTI electrical (Thickness (2) tested)        | 3            | mm                     | UL746B          |
| Relative Temperature Index - with impact     | 85           | °C                     | UL746B          |
| RTI with impact (Thickness (1) tested)       | 1.5          | mm                     | UL746B          |
| Relative Temperature Index - with impact     | 105          | °C                     | UL746B          |
| RTI with impact (Thickness (2) tested)       | 3            | mm                     | UL746B          |
| Relative Temperature Index - without impact  | 105          | °C                     | UL746B          |
| RTI without impact (Thickness (1) tested)    | 1.5          | mm                     | UL746B          |

DSM Product

Unlimited. DSM



# DSM Engineering Plastics - Property Data

## Xantar<sup>®</sup> MX 1000

PC-unfilled

|                                             |            |    |        |
|---------------------------------------------|------------|----|--------|
| Relative Temperature Index - without impact | <b>110</b> | °C | UL746B |
| RTI without impact (Thickness (2) tested)   | <b>3</b>   | mm | UL746B |

### ELECTRICAL PROPERTIES

|                                  |                 |       |             |
|----------------------------------|-----------------|-------|-------------|
| Relative permittivity (100Hz)    | <b>2.9</b>      | -     | IEC 60250   |
| Relative permittivity (1 MHz)    | <b>2.8</b>      | -     | IEC 60250   |
| Dissipation factor (100 Hz)      | <b>6.6</b>      | E-4   | IEC 60250   |
| Dissipation factor (1 MHz)       | <b>92</b>       | E-4   | IEC 60250   |
| Volume resistivity               | <b>&gt;1E13</b> | Ohm*m | IEC 60093   |
| Surface resistivity              | <b>&gt;1E15</b> | Ohm   | IEC 60093   |
| Electric strength                | <b>29</b>       | kV/mm | IEC 60243-1 |
| Comparative tracking index (PLC) | <b>2</b>        | class | UL 746A     |

### OTHER PROPERTIES

|                  |             |                   |                |
|------------------|-------------|-------------------|----------------|
| Water absorption | <b>0.35</b> | %                 | Sim. to ISO 62 |
| Density          | <b>1190</b> | kg/m <sup>3</sup> | ISO 1183       |

### RHEOLOGICAL CALCULATION PROPERTIES

|                              |             |         |   |
|------------------------------|-------------|---------|---|
| Thermal conductivity of melt | <b>0.26</b> | W/(m K) | - |
|------------------------------|-------------|---------|---|

