

Xantar[®] C RC 3710 (Provisional)

Property Data

(PC+ABS)...

Laser Direct Structuring, Vicat 120°C, Black color only

Properties	Typical Data	Unit	Test Method
RHEOLOGICAL PROPERTIES			
Melt volume-flow rate	15	cm ³ /10min	ISO 1133
Temperature	260	°C	ISO 1133
Load	5	kg	ISO 1133
Molding shrinkage (parallel)	0.6	%	ISO 294-4
MECHANICAL PROPERTIES			
Tensile modulus	2200	MPa	ISO 527-1/-2
Yield stress	50	MPa	ISO 527-1/-2
Yield strain	4	%	ISO 527-1/-2
Nominal strain at break	>50	%	ISO 527-1/-2
Flexural modulus	2250	MPa	ISO 178
Flexural strength	80	MPa	ISO 178
Charpy impact strength (+23°C)	N	kJ/m ²	ISO 179/1eU
Charpy impact strength (-30°C)	N	kJ/m ²	ISO 179/1eU
Izod notched impact strength (23°C)	60	kJ/m ²	ISO 180/4A
Izod notched impact strength (-20°C)	40	kJ/m ²	ISO 180/4A
THERMAL PROPERTIES			
Temp. of deflection under load (1.80 MPa)	105	°C	ISO 75-1/-2
Vicat softening temperature (50°C/h 50N)	120	°C	ISO 306
Coeff. of linear therm. expansion (parallel)	0.7	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.7	E-4/°C	ISO 11359-1/-2
OTHER PROPERTIES			
Water absorption	0.6	%	Sim. to ISO 62
Density	1210	kg/m ³	ISO 1183

a **DSM**Product

Unlimited. **DSM**

