

DSM Engineering Plastics - Property Data

Xantar® C MC 3433

(PC+ABS)-unfilled...

Flame retardant, high flow

Properties	Typical Data	Unit	Test Method
------------	--------------	------	-------------

RHEOLOGICAL PROPERTIES

Melt volume-flow rate	40	cm ³ /10min	ISO 1133
Temperature	260	°C	ISO 1133
Load	5	kg	ISO 1133
Molding shrinkage (parallel)	0.5	%	ISO 294-4

MECHANICAL PROPERTIES

Tensile modulus	2850	MPa	ISO 527-1/-2
Yield stress	60	MPa	ISO 527-1/-2
Yield strain	4	%	ISO 527-1/-2
Nominal strain at break	>50	%	ISO 527-1/-2
Charpy impact strength (+23°C)	N	kJ/m ²	ISO 179/1eU
Charpy impact strength (-30°C)	N	kJ/m ²	ISO 179/1eU
Flexural modulus	2800	MPa	ISO 178
Flexural strength	110	MPa	ISO 178
Izod notched impact strength (23°C)	45	kJ/m ²	ISO 180/4A

THERMAL PROPERTIES

Temp. of deflection under load (1.80 MPa)	90	°C	ISO 75-1/-2
Vicat softening temperature (50°C/h 50N)	104	°C	ISO 306
Burning Behav. at 1.6 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.5	mm	IEC 60695-11-10
Burning Behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	3	mm	IEC 60695-11-10
Oxygen index	32	%	ISO 4589-1/-2
Ball pressure temperature	90	°C	IEC 60695-10-2
Glow Wire Flammability Index GWFI	960	°C	IEC 60695-2-12
GWFI (Thickness (1) tested)	1.5	mm	IEC 60695-2-12
Glow Wire Flammability Index GWFI	960	°C	IEC 60695-2-12
GWFI (Thickness (2) tested)	3	mm	IEC 60695-2-12
Glow Wire Ignition Temperature GWIT	800	°C	IEC 60695-2-13
GWIT (Thickness (1) tested)	1.5	mm	IEC 60695-2-12
Glow Wire Ignition Temperature GWIT	775	°C	IEC 60695-2-13
GWIT (Thickness (2) tested)	3	mm	IEC 60695-2-12

ELECTRICAL PROPERTIES

Relative permittivity (1 MHz)	3	-	IEC 60250
Volume resistivity	>1E13	Ohm*m	IEC 60093
Surface resistivity	>1E15	Ohm	IEC 60093
Comparative tracking index	325	-	IEC 60112
Comparative tracking index (PLC)	2	class	UL 746A

DSM Product

Unlimited. DSM



Xantar[®] C MC 3433

(PC+ABS)-unfilled...

OTHER PROPERTIES

Water absorption	0.6	%	Sim. to ISO 62
Density	1170	kg/m ³	ISO 1183

RHEOLOGICAL CALCULATION PROPERTIES

Thermal conductivity of melt	0.23	W/(m K)	-
------------------------------	-------------	---------	---

