

DSM Engineering Plastics - Property Data

Stamylan® UH 210

PE-unfilled

Properties	Typical Data	Unit	Test Method
RHEOLOGICAL PROPERTIES			
Elongational Stress F(150/10)	0.23	MPa	ISO 11542-2/A
MECHANICAL PROPERTIES			
Tensile modulus	650	MPa	ISO 527-1/-2
Yield stress	19	MPa	ISO 527-1/-2
Yield strain	11	%	ISO 527-1/-2
Nominal strain at break	>50	%	ISO 527-1/-2
Abrasion resistance	100	%	DIN 16972
Charpy double-notched impact strength (23°C)	190	kJ/m ²	ISO 11542-2/B
THERMAL PROPERTIES			
Melting temperature (10°C/min)	133	°C	ISO 11357-1/-3
OTHER PROPERTIES			
Density	930	kg/m ³	ISO 1183
Apparent density	480	kg/m ³	ISO 60
Average particle size	150	m-6	-
MATERIAL SPECIFIC PROPERTIES			
Viscosity number	2200	cm ³ /g	ISO 307, 1157, 1628
Average molecular weight	4.60E6	g/mol	-

