

Arnite® A04 900

PET

Medium Viscosity, Nucleated, Food Contact Quality

Properties	Typical Data	Unit	Test Method
Rheological properties			
	Value		
Molding shrinkage [normal]	1.7	%	Sim. to ISO 294-4
Molding shrinkage [parallel]	1.7	%	Sim. to ISO 294-4
Mechanical properties			
	Value		
Tensile modulus	2800	MPa	ISO 527-1/-2
Yield stress	80	MPa	ISO 527-1/-2
Yield strain	4	%	ISO 527-1/-2
Nominal strain at break	12	%	ISO 527-1/-2
Charpy impact strength (+23°C)	N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	3	kJ/m ²	ISO 179/1eA
Thermal properties			
	Value		
Melting temperature (10°C/min)	255	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	80	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	115	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.7	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.7	E-4/°C	ISO 11359-1/-2
Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	IEC 60695-11-10
Burning Behav. at 3.0 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	3	mm	IEC 60695-11-10

Electrical properties

Value



Property Data

Arnite[®] A04 900

Properties	Typical Data	Unit	Test Method
Relative permittivity (100Hz)	3.3	-	IEC 62631-2-1
Relative permittivity (1 MHz)	3.2	-	IEC 62631-2-1
Dissipation factor (100 Hz)	20	E-4	IEC 62631-2-1
Dissipation factor (1 MHz)	21	E-4	IEC 62631-2-1
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1

Other properties

Value

Water absorption	0.5	%	Sim. to ISO 62
Humidity absorption	0.2	%	Sim. to ISO 62
Density	1370	kg/m ³	ISO 1183

