

# Arnite® AV2 365 SN

## PET-GF33 FR(17)

33% Glass Reinforced, Flame Retardant

| Properties                                   | Typical Data | Unit              | Test Method       |
|----------------------------------------------|--------------|-------------------|-------------------|
| <b>Rheological properties</b>                |              |                   |                   |
|                                              | Value        |                   |                   |
| Molding shrinkage [normal]                   | 1            | %                 | Sim. to ISO 294-4 |
| Molding shrinkage [parallel]                 | 0.5          | %                 | Sim. to ISO 294-4 |
| <b>Mechanical properties</b>                 |              |                   |                   |
|                                              | Value        |                   |                   |
| Tensile modulus                              | 13500        | MPa               | ISO 527-1/-2      |
| Stress at break                              | 165          | MPa               | ISO 527-1/-2      |
| Strain at break                              | 2            | %                 | ISO 527-1/-2      |
| Charpy impact strength (+23°C)               | 50           | kJ/m <sup>2</sup> | ISO 179/1eU       |
| Charpy impact strength (-30°C)               | 50           | kJ/m <sup>2</sup> | ISO 179/1eU       |
| Charpy notched impact strength (+23°C)       | 10           | kJ/m <sup>2</sup> | ISO 179/1eA       |
| Charpy notched impact strength (-30°C)       | 10           | kJ/m <sup>2</sup> | ISO 179/1eA       |
| <b>Thermal properties</b>                    |              |                   |                   |
|                                              | Value        |                   |                   |
| Melting temperature (10°C/min)               | 255          | °C                | ISO 11357-1/-3    |
| Temp. of deflection under load (1.80 MPa)    | 240          | °C                | ISO 75-1/-2       |
| Temp. of deflection under load (0.45 MPa)    | 250          | °C                | ISO 75-1/-2       |
| Coeff. of linear therm. expansion (parallel) | 0.2          | E-4/°C            | ISO 11359-1/-2    |
| Coeff. of linear therm. expansion (normal)   | 0.65         | E-4/°C            | ISO 11359-1/-2    |
| Burning Behav. at 1.5 mm nom. thickn.        | V-0          | class             | IEC 60695-11-10   |
| Thickness tested                             | 1.5          | mm                | IEC 60695-11-10   |
| Burning Behav. at 3.0 mm nom. thickn.        | V-0          | class             | IEC 60695-11-10   |
| Thickness tested                             | 3            | mm                | IEC 60695-11-10   |



## Property Data

# Arnite<sup>®</sup> AV2 365 SN

| Properties                    | Typical Data | Unit              | Test Method    |
|-------------------------------|--------------|-------------------|----------------|
| <b>Electrical properties</b>  |              |                   |                |
|                               | Value        |                   |                |
| Relative permittivity (100Hz) | 3.5          | -                 | IEC 62631-2-1  |
| Relative permittivity (1 MHz) | 3.8          | -                 | IEC 62631-2-1  |
| Dissipation factor (100 Hz)   | 10           | E-4               | IEC 62631-2-1  |
| Dissipation factor (1 MHz)    | 140          | E-4               | IEC 62631-2-1  |
| Volume resistivity            | >1E13        | Ohm*m             | IEC 62631-3-1  |
| Comparative tracking index    | 200          | V                 | IEC 60112      |
| <b>Other properties</b>       |              |                   |                |
|                               | Value        |                   |                |
| Water absorption              | 0.4          | %                 | Sim. to ISO 62 |
| Humidity absorption           | 0.12         | %                 | Sim. to ISO 62 |
| Density                       | 1750         | kg/m <sup>3</sup> | ISO 1183       |

