

ForTii® MX2

PPA-GF40

40% Glass Reinforced, PA4T, Heat Stabilized, for Automotive applications

ForTii® MX2 is a high Tg PPA that outperforms in dimensional stability at elevated temperatures due to the high heat deflection temperature (HDT). MX2 has excellent fatigue performance and good chemical resistance.

Properties	Typical Data	Unit	Test Method
Rheological properties			
	dry / cond		
Molding shrinkage (parallel)	0.35 / *	%	ISO 294-4
Molding shrinkage (normal)	1 / *	%	ISO 294-4
Mechanical properties			
	dry / cond		
Tensile modulus	14500 / 14800	MPa	ISO 527-1/-2
Tensile modulus (-40°C)	14800 / 15000	MPa	ISO 527-1/-2
Tensile modulus (40°C)	14200 / 14000	MPa	ISO 527-1/-2
Tensile modulus (80°C)	13500 / 8800	MPa	ISO 527-1/-2
Tensile modulus (100°C)	12800 / 7000	MPa	ISO 527-1/-2
Tensile modulus (120°C)	9500 / 6300	MPa	ISO 527-1/-2
Tensile modulus (150°C)	6700	MPa	ISO 527-1/-2
Tensile modulus (160°C)	6300	MPa	ISO 527-1/-2
Tensile modulus (180°C)	5500	MPa	ISO 527-1/-2
Tensile modulus (200°C)	5300	MPa	ISO 527-1/-2
Stress at break	230 / 210	MPa	ISO 527-1/-2
Stress at break (-40°C)	250 / 250	MPa	ISO 527-1/-2
Stress at break (40°C)	220 / 190	MPa	ISO 527-1/-2
Stress at break (80°C)	200 / 115	MPa	ISO 527-1/-2
Stress at break (100°C)	170 / 100	MPa	ISO 527-1/-2
Stress at break (120°C)	140 / 90	MPa	ISO 527-1/-2



Properties	Typical Data	Unit	Test Method
Stress at break (150°C)	105	MPa	ISO 527-1/-2
Stress at break (160°C)	95	MPa	ISO 527-1/-2
Stress at break (180°C)	85	MPa	ISO 527-1/-2
Stress at break (200°C)	78	MPa	ISO 527-1/-2
Strain at break	2.3 / 2.2	%	ISO 527-1/-2
Strain at break (-40°C)	2.2 / 2.1	%	ISO 527-1/-2
Strain at break (40°C)	2.2 / 2.1	%	ISO 527-1/-2
Strain at break (80°C)	2.5 / 4.5	%	ISO 527-1/-2
Strain at break (100°C)	3 / 5	%	ISO 527-1/-2
Strain at break (120°C)	5.1 / 6	%	ISO 527-1/-2
Strain at break (150°C)	6.9	%	ISO 527-1/-2
Strain at break (160°C)	7	%	ISO 527-1/-2
Strain at break (180°C)	7	%	ISO 527-1/-2
Strain at break (200°C)	7	%	ISO 527-1/-2
Flexural modulus	14000 / 14500	MPa	ISO 178
Flexural strength	350 / 290	MPa	ISO 178
Flexural modulus (120°C)	9800	MPa	ISO 178
Flexural modulus (160°C)	6000	MPa	ISO 178
Flexural modulus (180°C)	5400	MPa	ISO 178
Flexural modulus (200°C)	5000	MPa	ISO 178
Charpy impact strength (+23°C)	70 / 60	kJ/m ²	ISO 179/1eU
Charpy impact strength (-30°C)	65 / 55	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	11 / 9	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	10 / 8	kJ/m ²	ISO 179/1eA

Thermal properties

dry / cond

Melting temperature (10°C/min)	325 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	305 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.3	E-4/°C	ASTM D696
Coeff. of linear therm. expansion (normal)	0.35	E-4/°C	ASTM D696



ForTii[®] MX2

Properties	Typical Data	Unit	Test Method
Thermal Index 5000 hrs	175	°C	IEC 60216/ISO 527-1/-2
Electrical properties dry / cond			
Volume resistivity	>1E13 / >1E13	Ohm*m	IEC 62631-3-1
Relative permittivity (100Hz)	4.9 / 5.7	-	IEC 62631-2-1
Relative permittivity (1 MHz)	4.6 / 4.8	-	IEC 62631-2-1
Other properties dry / cond			
Humidity absorption	1.8 / *	%	Sim. to ISO 62
Density	1550 / -	kg/m ³	ISO 1183

Tens. fatigue 8Hz, T, R=0.1 ,
dry

