

UDea™ ForTii® Ace X20G60

PPA-GF60

60% Continuous Glass Fiber Reinforced, Uni-Directional Tape, Black

Properties	Typical Data	Unit	Test Method
General physical properties	dry / cond		
Density	1770 / -	kg/m ³	ISO 1183
Fiber content (V/V)	41	%	ISO 11667
Physical tape properties	Value		
Areal weight - Tape	420	g/m ²	ISO 1172
Thickness - Tape	0.25	mm	
Mechanical tape properties	dry / cond		
Tensile modulus - 0° - Tape	* / 33	GPa	ISO 527-4/-5
Stress at break - 0° - Tape	* / 760	MPa	ISO 527-4/-5
Strain at break - 0° - Tape	2.6 /	%	ISO 527-4/-5
Thermal properties	dry / cond		
Melting temperature (10°C/min)	320 / *	°C	ISO 11357-1/-3
Other properties	dry / cond		
Humidity absorption	1.1 / *	%	Sim. to ISO 62

