

UDea™ Xytron™ R20C50

PPS-CF50

50% Continuous Carbon Fiber Reinforced, Uni-Directional Tape, Black

Properties	Typical Data	Unit	Test Method
Thermal properties	dry / cond		
Melting temperature (10°C/min)	280 / *	°C	ISO 11357-1/-3
Other properties	dry / cond		
Density	1400 / -	kg/m ³	ISO 1183
Humidity absorption	0.02 / *	%	Sim. to ISO 62

