

Xytron™ G4010T

PPS-GF40

40% Glass Reinforced, Flame Retardant, Improved flow

Properties	Typical Data	Unit	Test Method
Rheological properties			
	Value		
Molding shrinkage (parallel)	0.2	%	ISO 294-4
Molding shrinkage (normal)	0.5	%	ISO 294-4
Mechanical properties			
	Value		
Tensile modulus	15000	MPa	ISO 527-1/-2
Tensile modulus (120°C)	7300	MPa	ISO 527-1/-2
Tensile modulus (160°C)	5200	MPa	ISO 527-1/-2
Tensile modulus (200°C)	3400	MPa	ISO 527-1/-2
Stress at break	200	MPa	ISO 527-1/-2
Stress at break (120°C)	105	MPa	ISO 527-1/-2
Stress at break (160°C)	73	MPa	ISO 527-1/-2
Stress at break (200°C)	55	MPa	ISO 527-1/-2
Strain at break	2	%	ISO 527-1/-2
Strain at break (120°C)	3.1	%	ISO 527-1/-2
Strain at break (160°C)	3.9	%	ISO 527-1/-2
Strain at break (200°C)	6.4	%	ISO 527-1/-2
Flexural modulus	14500	MPa	ISO 178
Flexural strength	300	MPa	ISO 178
Flexural modulus (120°C)	10000	MPa	ISO 178
Flexural modulus (160°C)	5000	MPa	ISO 178
Flexural modulus (200°C)	4200	MPa	ISO 178
Charpy impact strength (+23°C)	56	kJ/m ²	ISO 179/1eU
Charpy impact strength (-30°C)	57	kJ/m ²	ISO 179/1eU



Xytron™ G4010T

Properties	Typical Data	Unit	Test Method
Charpy notched impact strength (+23°C)	10	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	10	kJ/m ²	ISO 179/1eA
Izod impact strength (+23°C)	48	kJ/m ²	ISO 180/1U
Izod notched impact strength (+23°C)	10.5	kJ/m ²	ISO 180/1A
Rockwell hardness, R scale	121	-	ISO 2039-2
Rockwell hardness, M scale	100	-	ISO 2039-2

Thermal properties

Value

Melting temperature (10°C/min)	280	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	265	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.15	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.4	E-4/°C	ISO 11359-1/-2
Coef. of lin. therm expansion, parallel, above Tg	0.15	E-4/°C	ISO 11359-1/-2
Coef. of lin. therm expansion, normal, above Tg	1.1	E-4/°C	ISO 11359-1/-2
Burning Behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.5	mm	IEC 60695-11-10
UL recognition	Yes	-	-
Burning Behav. at 3.0 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	3	mm	IEC 60695-11-10
UL recognition	Yes	-	-
Relative Temperature Index - electrical	130	°C	UL746B
RTI electrical (Thickness (1) tested)	0.8	mm	UL746B

Electrical properties

Value

Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Electric strength	31	kV/mm	IEC 60243-1
Comparative tracking index	175	V	IEC 60112
Dissipation factor (5GHz)	55	E-4	IEC 60250
Relative permittivity (5GHz)	4	-	IEC 60250



Property Data

Xytron™ G4010T

Properties	Typical Data	Unit	Test Method
Other properties	Value		
Density	1650	kg/m ³	ISO 1183
Humidity absorption	0.04	%	Sim. to ISO 62

