

Arnitel® EL550-08

TPC-ET

Injection Molding, Food Contact Quality

Properties	Typical Data	Unit	Test Method
Rheological properties			
	Value		
Melt volume-flow rate	23	cm ³ /10min	ISO 1133
Temperature	230	°C	ISO 1133
Load	2.16	kg	ISO 1133
Molding shrinkage [parallel]	1.55	%	Sim. to ISO 294-4
Molding shrinkage [normal]	1.55	%	Sim. to ISO 294-4
Mechanical properties			
	Value		
Shore D Hardness (3s)	54	-	ISO 868
Tensile modulus	210	MPa	ISO 527-1/-2
Stress at break	35	MPa	ISO 527-1/-2
Nominal strain at break	620	%	ISO 527-1/-2
Stress at 5% strain	8.8	MPa	ISO 527-1/-2
Stress at 10% strain	12.8	MPa	ISO 527-1/-2
Stress at 50% strain	14.6	MPa	ISO 527-1/-2
Stress at 100% strain	14.6	MPa	ISO 527-1/-2
Charpy notched impact strength (+23°C)	N	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	25	kJ/m ²	ISO 179/1eA
Izod notched impact strength (+23°C)	N	kJ/m ²	ISO 180/1A
Izod notched impact strength (-20°C)	N	kJ/m ²	ISO 180/1A
Flexural modulus	230	MPa	ISO 178
Compression Set under constant strain at 70 °C	40	%	ISO 815

Mechanical properties (die cutting)

Value



Arnitel[®] EL550-08

Properties	Typical Data	Unit	Test Method
Stress at break (normal)	39	MPa	ISO 527-1/-2
Tear strength (normal)	153	kN/m	ISO 34-1; Method B
Tear strength (parallel)	152	kN/m	ISO 34-1; Method B
Strain at break (normal)	810	%	ISO 527-1/-2

Thermal properties

Value

Melting temperature (10°C/min)	204	°C	ISO 11357-1/-3
Temp. of deflection under load (0.45 MPa)	110	°C	ISO 75-1/-2
Vicat softening temperature (50°C/h 50N)	90	°C	ISO 306
Coeff. of linear therm. expansion (parallel)	2	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	2	E-4/°C	ISO 11359-1/-2

Electrical properties

Value

Relative permittivity (100Hz)	4.4	-	IEC 62631-2-1
Relative permittivity (1 MHz)	4	-	IEC 62631-2-1
Dissipation factor (1 MHz)	400	E-4	IEC 62631-2-1
Volume resistivity	1E11	Ohm*m	IEC 62631-3-1
Electric strength	21	kV/mm	IEC 60243-1
Comparative tracking index	600	V	IEC 60112

Other properties

Value

Density	1200	kg/m ³	ISO 1183
Water absorption	0.65	%	Sim. to ISO 62
Humidity absorption	0.2	%	Sim. to ISO 62

