

Arnitel® EM400-08

TPC-ET

Injection Molding or Extrusion Grade, Food Contact Quality

Properties	Typical Data	Unit	Test Method
Rheological properties			
	Value		
Melt flow index MFI	32	g/10min	ISO 1133
MFI test load	2.16	kg	ISO 1133
MFI test temperature	230	°C	ISO 1133
Molding shrinkage [parallel]	1.5	%	Sim. to ISO 294-4
Molding shrinkage [normal]	1.5	%	Sim. to ISO 294-4
Mechanical properties			
	Value		
Shore D Hardness (15s)	33	-	ISO 868
Tensile modulus	40	MPa	ISO 527-1/-2
Yield stress	6	MPa	ISO 527-1/-2
Yield strain	50	%	ISO 527-1/-2
Stress at break	20	MPa	ISO 527-1/-2
Stress at 10% strain	3	MPa	ISO 527-1/-2
Stress at 100% strain	6.6	MPa	ISO 527-1/-2
Charpy notched impact strength (+23°C)	N	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	N	kJ/m ²	ISO 179/1eA
Izod notched impact strength (+23°C)	N	kJ/m ²	ISO 180/1A
Izod notched impact strength (-20°C)	N	kJ/m ²	ISO 180/1A
Thermal properties			
	Value		
Melting temperature (10°C/min)	195	°C	ISO 11357-1/-3

Other properties

Value



Property Data

Arnitel[®] EM400-08

Properties	Typical Data	Unit	Test Method
Density	1110	kg/m ³	ISO 1183

