

Arnitel® EL150/U

TPC-ET

Injection Molding, UV Stabilized

Arnitel EL150/U is a very low modulus grade with nominal hardness of 20D. Material can be processed by many conventional thermoplastics processing techniques such as injection molding.

It is important to note that in a certain periods, clumps can be formed due to excessive storage conditions such as packing type, stacking, extreme temperature. Pl. refer injection molding recommendations

Food contact use – Not Applicable.

Properties	Typical Data	Unit	Test Method
Rheological properties			
	Value		
Melt volume-flow rate	77	cm ³ /10min	ISO 1133
Temperature	230	°C	ISO 1133
Load	2.16	kg	ISO 1133
Molding shrinkage [parallel]	0.7	%	Sim. to ISO 294-4
Molding shrinkage [normal]	1	%	Sim. to ISO 294-4
Mechanical properties			
	Value		
Shore D Hardness (3s)	19	-	ISO 868
Shore D Hardness (15s)	18	-	ISO 868
Shore A Hardness (3s)	80	-	ISO 868
Shore A Hardness (15s)	79	-	ISO 868
Tensile modulus	14	MPa	ISO 527-1/-2
Stress at break	13.8	MPa	ISO 527-1/-2
Nominal strain at break	980	%	ISO 527-1/-2
Stress at 5% strain	0.8	MPa	ISO 527-1/-2
Stress at 10% strain	1.4	MPa	ISO 527-1/-2
Stress at 50% strain	3.1	MPa	ISO 527-1/-2



Property Data (Provisional)

Arnitel[®] EL150/U

Properties	Typical Data	Unit	Test Method
Stress at 100% strain	3.8	MPa	ISO 527-1/-2
Thermal properties	Value		
Melting temperature (10°C/min)	165	°C	ISO 11357-1/-3
Other properties	Value		
Density	1060	kg/m ³	ISO 1183
Humidity absorption	0.12	%	Sim. to ISO 62

