

Arnitel® EM630-H

TPC-ET

Extrusion Grade, Heat Stabilized

Properties	Typical Data	Unit	Test Method
Rheological properties			
	Value		
Melt volume-flow rate	3.7	cm ³ /10min	ISO 1133
Temperature	230	°C	ISO 1133
Load	2.16	kg	ISO 1133
Mechanical properties			
	Value		
Shore D Hardness (3s)	59	-	ISO 868
Tensile modulus	275	MPa	ISO 527-1/-2
Stress at break	27	MPa	ISO 527-1/-2
Nominal strain at break	220	%	ISO 527-1/-2
Stress at 5% strain	12	MPa	ISO 527-1/-2
Stress at 10% strain	17	MPa	ISO 527-1/-2
Stress at 50% strain	21	MPa	ISO 527-1/-2
Stress at 100% strain	21	MPa	ISO 527-1/-2
Charpy notched impact strength (+23°C)	N	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	12	kJ/m ²	ISO 179/1eA
Izod notched impact strength (+23°C)	N	kJ/m ²	ISO 180/1A
Flexural modulus	305	MPa	ISO 178
Mechanical properties (die cutting)			
	Value		
Stress at break (normal)	52	MPa	ISO 527-1/-2
Tear strength (normal)	156	kN/m	ISO 34-1; Method B
Tear strength (parallel)	168	kN/m	ISO 34-1; Method B
Strain at break (normal)	750	%	ISO 527-1/-2



Property Data

Arnitel[®] EM630-H

Properties	Typical Data	Unit	Test Method
Thermal properties			
	Value		
Melting temperature (10°C/min)	212	°C	ISO 11357-1/-3
Vicat softening temperature (50°C/h 50N)	125	°C	ISO 306
Vicat softening temperature (50°C/h 10N)	200	°C	ISO 306
Coeff. of linear therm. expansion (parallel)	1.5	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	1.5	E-4/°C	ISO 11359-1/-2
Electrical properties			
	Value		
Relative permittivity (1 MHz)	4.1	-	IEC 62631-2-1
Dissipation factor (1 MHz)	170	E-4	IEC 62631-2-1
Volume resistivity	1.2E11	Ohm*m	IEC 62631-3-1
Electric strength	22	kV/mm	IEC 60243-1
Comparative tracking index	600	V	IEC 60112
Other properties			
	Value		
Density	1240	kg/m ³	ISO 1183
Water absorption	0.63	%	Sim. to ISO 62
Humidity absorption	0.18	%	Sim. to ISO 62

