

DSM Engineering Plastics - Property Data

Arnitel® EM400

TPE-unfilled

34 Shore D, Injection or Extrusion Grade

Properties	Typical Data	Unit	Test Method
------------	--------------	------	-------------

RHEOLOGICAL PROPERTIES

Melt volume-flow rate	30	cm ³ /10min	ISO 1133
Temperature	230	°C	ISO 1133
Load	2.16	kg	ISO 1133

MECHANICAL PROPERTIES

Shore D Hardness (3s)	34	-	ISO 868
Tensile modulus	50	MPa	ISO 527-1/-2
Stress at break	25	MPa	ISO 527-1/-2
Stress at 5% strain	2.4	MPa	ISO 527-1/-2
Stress at 10% strain	3.9	MPa	ISO 527-1/-2
Stress at 50% strain	6.9	MPa	ISO 527-1/-2
Stress at 100% strain	7.5	MPa	ISO 527-1/-2
Charpy notched impact strength (+23°C)	N	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	N	kJ/m ²	ISO 179/1eA
Izod notched impact strength (23°C)	N	kJ/m ²	ISO 180/1A
Tear strength Graves (without nick)	60	kN/m	ISO 34

THERMAL PROPERTIES

Melting temperature (10°C/min)	195	°C	ISO 11357-1/-3
Vicat softening temperature (50°C/h 10N)	140	°C	ISO 306
Coeff. of linear therm. expansion (parallel)	2.2	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	2.2	E-4/°C	ISO 11359-1/-2
Burning Behav. at 1.6 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	IEC 60695-11-10

ELECTRICAL PROPERTIES

Relative permittivity (100Hz)	4.1	-	IEC 60250
Relative permittivity (1 MHz)	4	-	IEC 60250
Dissipation factor (100 Hz)	10	E-4	IEC 60250
Dissipation factor (1 MHz)	170	E-4	IEC 60250
Volume resistivity	1E13	Ohm*m	IEC 60093
Surface resistivity	>1E15	Ohm	IEC 60093
Electric strength	20	kV/mm	IEC 60243-1
Comparative tracking index	600	-	IEC 60112

OTHER PROPERTIES

Density	1110	kg/m ³	ISO 1183
Water absorption	0.75	%	Sim. to ISO 62
Humidity absorption	0.3	%	Sim. to ISO 62

DSM Product

Unlimited. DSM

