

DSM Engineering Plastics - Property Data

Arnitel® EM630-H

TPE-unfilled

Properties	Typical Data	Unit	Test Method
RHEOLOGICAL PROPERTIES			
Melt volume-flow rate	4.7	cm ³ /10min	ISO 1133
Temperature	240	°C	ISO 1133
Load	2.16	kg	ISO 1133
MECHANICAL PROPERTIES			
Tensile modulus	310	MPa	ISO 527-1/-2
Stress at 10% strain	15.9	MPa	ISO 527-1/-2
Stress at 100% strain	15.8	MPa	ISO 527-1/-2
Charpy notched impact strength (+23°C)	N	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	12	kJ/m ²	ISO 179/1eA
THERMAL PROPERTIES			
Melting temperature (10°C/min)	212	°C	ISO 11357-1/-3
Vicat softening temperature (50°C/h 50N)	125	°C	ISO 306
Coeff. of linear therm. expansion (parallel)	1.5	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	1.5	E-4/°C	ISO 11359-1/-2
Burning Behav. at 1.6 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	IEC 60695-11-10
ELECTRICAL PROPERTIES			
Relative permittivity (1 MHz)	4.1	-	IEC 60250
Dissipation factor (1 MHz)	170	E-4	IEC 60250
Volume resistivity	1.20E11	Ohm*m	IEC 60093
Surface resistivity	2.50E14	Ohm	IEC 60093
Electric strength	22	kV/mm	IEC 60243-1
Comparative tracking index	600	-	IEC 60112
OTHER PROPERTIES			
Density	1230	kg/m ³	ISO 1183
Water absorption	0.63	%	Sim. to ISO 62
Humidity absorption	0.18	%	Sim. to ISO 62

DSM Product

Unlimited. **DSM**

