

A NSF\* certified, low hardness and multi-purpose thermoplastic elastomer featuring excellent fluid resistance and high temperature performance. It can be processed by injection molding, blow molding or extrusion for applications in contact with potable water, such as pipes, fittings and appurtenances.

Typical Properties**	Test Method	S.I.		U.S.	
		Typical Value	Units	Typical Value	Units
<b>Hardness shore A (5 sec)</b>	ASTM D-2240				
Injection moulded sample	5 sec. delay	84		84	
Extruded sample	5 sec. delay	80		80	
<b>Specific gravity</b>	ASTM D-792	0.95		0.95	
<b>Stress/strain properties</b>	ASTM D-412				
Flow direction	Die C				
Tensile strength		7.1	MPa	1030	Psi
Modulus 100%		5.1	MPa	740	Psi
Elongation at break		430	%	430	%
Cross direction					
Tensile strength		9.3	MPa	1349	Psi
Modulus 100%		4.5	MPa	653	Psi
Elongation at break		676	%	676	%
<b>Tear strength</b>	ASTM D-624				
Cross direction	Die C				
Unnicked		51	kN/m	291	Pli
<b>Compression set</b>	ASTM D-395				
22h/23°C	Method B	32	%	32	%
22h/70°C		46	%	46	%
22h/100°C		52	%	52	%

\* Complies with NSF standards 61: Piping related system components for drinking water with surface area to volume ratio of 100 square inches per liter at hot temperature.

\*\* Tests are conducted on injection molded plaques unless indicated otherwise.



Certified to  
ANSI/NSF 61



Sarlink® 3480 is a polypropylene based elastomer, which can be processed on conventional thermoplastic equipment for injection molding and extrusion. This product has a wide processing window in most applications. Melt temperatures from 360°-430°F can be used. Do not exceed 450°F. Drying is recommended for extrusion and blow molding and any time the material is used from an unsealed package. Dry three (3) hours at 180°F.

INJECTION MOULDING CONDITIONS			EXTRUSION CONDITIONS		
Melt temperature		360-430°F	Melt temperature		380-420°F
Barrel Temperatures	Rear Middle Front Nozzle	350-420°F 350-420°F 350-420°F 370-430°F	Barrel Temperatures	Rear Transition Metered Front Die	360-400°F 360-400°F 370-410°F 370-410°F 380-420°F
Mold Temperature		50-150°F			
Screw Speed		100-200 RPM	Roll Temperatures		70-120°F
Back Pressure		10-150 psi	Screen Pack		20 to 60 mesh
Screw	General Purpose 20:1 L/D ratio		Screw	General Purpose 3:1 compression ratio	

#### PURGING

Sarlink® 3480 has excellent melt stability. Empty the barrel for idle periods of thirty (30) minutes or longer. Purge thoroughly before and after use of this product with polyethylene or polypropylene.

#### RECYCLING/REGRIND

This product can be reprocessed. Physical properties are generally not degraded. Dry regrind prior to reprocessing.

#### COLORING

The use of polyolefin based color concentrates is recommended. Apply back pressure in injection molding prior to disperse color.

#### BONDING/ASSEMBLY

Thermal bonding techniques can be used to form high strength bonds. Adhesive bonding can be achieved with specialized adhesives. Bond strength is limited due to the polypropylene base of this material.

#### STORAGE & HANDLING

Sarlink® 3480 is available in 55 lb. foil lined bags (up to 2,200 lbs. per pallet) or 1,100 lb. polyethylene lined gaylords. It has a storage life at normal temperatures of several years. Please refer to the Material Safety Data Sheet for this grade prior to first time handling.

DSM Thermoplastic Elastomers Inc. is an ISO 9001 registered company  
Sarlink® is a registered trademark of DSM, The Netherlands

