+135-3858-6433 (GuangDong) +188-1699-6168 (ShangHai) +852-6957-5415 (HongKong)

# **PLATAMID®**

## M 1943 PELLETS

### Platamid® M 1943 Pellets

Copolyamide Hot Melt Adhesive /Extrusion Applications

**Platamid® M 1943 Pellets** is a standard thermoplastic copolyamide hot melt adhesive available in pellet form. This medium melt viscosity, low re-crystallizing grade, is particularly suitable for manufacturing webs, nets, mono- and multi-filaments and films by extrusion.

Platamid® M 1943 Pellets offer very good adhesion to various polar substrates (thermoplastics, thermosets, metal, natural fibers, etc).

PROPERTIES	DRY / COND	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Volume-Flow Rate	10 / *	cm³/10min	ISO 1133
Temperature	160 / *	°C	-
	320 / *	°F	
Load	2.16 / *	kg	-
	4.76 / *	lb	
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	122 / *	°C	ISO 11357-1/-3

### **AVAILABLE GRADES**

This grade is available:

- dried with optical brightener (M 1943 TA)

## **PACKAGING**

Platamid<sup>®</sup> M 1943 is delivered in 25 kg sealed bags.

This grade are ready to be processed

#### SHELFLIFE

Two years from the date of delivery. For any use above this limit, please refer to our technical services.

RENEWABLE CARBON CONTENT: 26 % (Internal method)



+135-3858-6433 (GuangDong) +188-1699-6168 (ShangHai) +852-6957-5415 (HongKong)

# **PLATAMID®**

# **M 1943 PELLETS**

PROCESSING
Film Extrusion, Melt Spinning, Web Processing
DELIVERY FORM
Pellets
SPECIAL CHARACTERISTICS
Adhesive, Bio-Based
REGIONAL AVAILABILITY
North America, Europe, Asia Pacific, South and Central America, Near East/Africa

