

TECHNICAL DATA SHEET

RILSAN® BESNO P40 TLO

POLYAMIDE 11 PELLET

RILSAN® BESNO P40 TLO is a polyamide 11 compound. It is produced from a renewable & sustainable source (castor oil). This natural plasticized grade is designed for tube extrusion, with a particularly low amount of oligomers.

Designation : ISO 16396 - PA11-P, EG1HL, C22-003

TYPE

PA11-P

MAIN APPLICATIONS

- Upstream - Bonded Pipes
- Upstream - Onshore - Growth
- Upstream - Offshore Flexible Pipes
- Cable
- Auto - In Tank & Fuel Venting Lines
- Auto - Gasoline Lines

DELIVERY FORM

- Pellets

TRANSFORMATION PROCESSES

- Extrusion - General
- Tube Extrusion

ADDITIVES

- Heat Stabilized
- Light Stabilized
- Plasticizer

MECHANICAL PROPERTIES

PROPERTIES	DRY / COND VALUE*	UNIT	TEST STANDARD
Hardness, Shore D, 15 s	- / 60		ISO 868
Charpy unnotched impact strength, 23°C (73°F)	- / No Break		ISO 179 1eU
Charpy unnotched impact strength, -30°C (-22°F)	- / No Break		ISO 179 1eU
Nominal strain at break, 23°C (73°F), 50 mm/min	- / > 50	%	ISO 527-1/-2
Yield strain, 23°C (73°F), 50 mm/min	- / 46	%	ISO 527-1/-2
Yield stress, 23°C (73°F), 50 mm/min	- / 26	MPa	ISO 527-1/-2
Tensile modulus, 23°C (73°F), 1 mm/min	- / 310	MPa	ISO 527-1/-2
Charpy notched impact strength, 23°C (73°F)	No Break / No Break		ISO 179 1eA
Charpy notched impact strength, -30°C (-22°F)	- / 6	kJ/m2	ISO 179 1eA
Flexural modulus, 23°C (73°F)	- / 300	MPa	ISO 178

*DRY: Dry As Molded (DAM) if pellet / Dry if powder.
COND: Conditionned.

THERMAL PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Melting temperature, 10°C/min	182	°C	ISO 11357-1/-3

OTHER PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Specific gravity, 23°C (73°F)	1.04	g/cm³	ISO 1183-1

RILSAN® BESNO P40 TLO

PACKAGING

Available packaging:

- 25 kg / 55 lb bags
- 550 kg rigid containers

SHELF LIFE

Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

PROCESSING CONDITIONS:

- Typical melt temperature (Min / Recommended / Max) - Injection Molding: 230°C / 250°C / 270°C (445°F / 480°F / 520°F)
- Typical mold temperature - Injection molding: 20-60°C (70-140°F)
- Drying time and temperature: 80-90°C (175-195°F) / 4-6 hours

SPECIAL CHARACTERISTICS

- Bio-based
- Low oligomers