

RILSAN® BESNO P40 TLX

PA11-P, EHL, 22-003

Rilsan® BESNO P40 TLX resin is a polyamide 11 produced from a renewable source. This natural grade is plasticized and designed for extrusion of large pipe as used in Oil and Gaz applications.

The percentage of renewable carbon according to ASTM D 6866 (calculated) is >89%.

PROPERTIES	DRY / COND	UNIT	TEST STANDARD
MECHANICAL PROPERTIES			
Tensile Modulus	- / 345	MPa	ISO 527-1/-2
	- /	psi	
Yield stress	50000 - / 26	MPa	ISO 527-1/-2
	- / 3770	psi	
Yield strain	- / 50	%	ISO 527-1/-2
Nominal Strain at Break	- / >50	%	ISO 527-1/-2
Shore D Hardness	60 / *	-	ISO 868
Charpy Impact Strength, +23°C	- / No Break	kJ/m²	ISO 179/1eU
Charpy Impact Strength, -30°C	- / No Break	kJ/m²	ISO 179/1eU
Charpy Notched Impact Strength, +23°C	- / No Break	kJ/m²	ISO 179/1eA
Charpy Notched Impact Strength, -30°C	- / 7	kJ/m²	ISO 179/1eA
	- / 3.33	ftlb/in²	
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	181 / *	°C	ISO 11357-1/-3
OTHER PROPERTIES			
Water Absorption	1.6 / *	%	Sim. to ISO 62
Density	1040 / 1040	kg/m³	ISO 1183
	1.04 / 1.04	g/cm³	
%Bio-Based	89	-	ASTM D6866

MAIN APPLICATIONS:

- Fluid transportation for Oil and Gaz sector
- Pressure and external sheath for offshore flexible pipe as per API 17 J
- Liner for steel tubes or composite pipes

PACKAGING:

This grade is delivered dried in sealed packaging (44 lb bags, 550 kg rigid containers, 1000 lb rigid containers) ready to be processed.

RILSAN® BESNO P40 TLX

SHELF LIFE:

Two years from the delivery. For any use above this limit, please refer to our technical services.

Processing conditions:

- Typical melt temperature (Min / Recommended / Max) : 230°C / 250°C / 280°C.

- Drying time and temperature (only necessary for bags opened for more than two hours) : 4-8 hours at 80-90°C.

PROCESSING

Profile Extrusion, Other Extrusion

DELIVERY FORM

Pellets

ADDITIVES

Lubricants, Plasticizer

SPECIAL CHARACTERISTICS

Bio-Based, Heat Stabilized, Light Stabilized

REGIONAL AVAILABILITY

North America, Europe, Asia Pacific, South and Central
America, Near East/Africa