

TECHNICAL DATA SHEET

RILSAN® BESN G9 TL

POLYAMIDE 11 PELLET

RILSAN® BESN G9 TL is a polyamide 11 compound. It is produced from a renewable & sustainable source (castor oil). This black grade with improved friction properties is designed for tube extrusion.

Designation : ISO 16396 - PA11, CDx, EG1HLS, C22-020

TYPE

PA11

MAIN APPLICATIONS

- Hoses & Tubes
- Industry - Distribution
- Auto - Others Extrusion
- Auto - Others Injection

DELIVERY FORM

- Pellets

TRANSFORMATION PROCESSES

- Extrusion - General
- Tube Extrusion

ADDITIVES

- Heat Stabilized
- Light Stabilized
- Lubricants

RHEOLOGICAL PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Melt volume flow rate (MVR), 235°C / 2.16 kg (455°F / 4.4 lb)	1	cm³/10min	ISO 1133

MECHANICAL PROPERTIES

PROPERTIES	DRY / COND VALUE*	UNIT	TEST STANDARD
Hardness, Shore D, 15 s	- / 71		ISO 868
Charpy unnotched impact strength, 23°C (73°F)	No Break / No Break		ISO 179 1eU
Charpy unnotched impact strength, -30°C (-22°F)	- / No Break		ISO 179 1eU
Nominal strain at break, 23°C (73°F), 50 mm/min	- / > 50	%	ISO 527-1/-2
Yield strain, 23°C (73°F), 50 mm/min	- / 5	%	ISO 527-1/-2
Yield stress, 23°C (73°F), 50 mm/min	46 / 46	MPa	ISO 527-1/-2
Tensile modulus, 23°C (73°F), 1 mm/min	2130 / 2130	MPa	ISO 527-1/-2
Charpy notched impact strength, 23°C (73°F)	- / 7	kJ/m2	ISO 179 1eA
Charpy notched impact strength, -30°C (-22°F)	- / 6	kJ/m2	ISO 179 1eA
Flexural modulus, 23°C (73°F)	- / 1790	MPa	ISO 178

*DRY: Dry As Molded (DAM) if pellet / Dry if powder.
COND: Conditioned.

RILSAN® BESN G9 TL

THERMAL PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Vicat softening temperature, 50N at 50°C/h	162	°C	ISO 306
Heat deflection temperature, 0.45 MPa	168	°C	ISO 75-1/-2
Heat deflection temperature, 1.8 MPa	56	°C	ISO 75-1/-2
Melting temperature, 10°C/min	186	°C	ISO 11357-1/-3

ELECTRICAL PROPERTIES

PROPERTIES	DRY / COND VALUE*	UNIT	TEST STANDARD
Surface resistivity, 23°C (73°F)	- / 6.0E+13	Ohm/sq	IEC 62631-3-2
Volumic (transversal) resistivity, 23°C (73°F)	- / 5.0E+11	Ohm.m	IEC 62631-3-1
Comparative tracking index, 23°C (73°F)	- / 600		IEC 60112
Dielectric stress, 23°C (73°F)	- / 55	kV/mm	IEC 60243-1

*DRY: Dry As Molded (DAM) if pellet / Dry if powder.
COND: Conditionned.

OTHER PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Water absorption, 23°C (73°F), immersion, equilibrium	1.7	%	ISO 62
Specific gravity, 23°C (73°F)	1.09	g/cm ³	ISO 1183-1

PACKAGING

Available packaging:

- 25 kg / 55 lb bags

SHELF LIFE

Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

PROCESSING CONDITIONS:

- Typical melt temperature (Min / Recommended / Max) - Injection Molding: 230°C / 250°C / 270°C (445°F / 480°F / 520°F)
- Typical mold temperature - Injection molding: 20-60°C (70-140°F)
- Drying time and temperature: 80-90°C (175-195°F) / 4-6 hours

SPECIAL CHARACTERISTICS

- Bio-based
- Low oligomers

RILSAN® BESN G9 TL

DIAGRAMS

