

TECHNICAL DATA SHEET

RILSAN® BMNO SG FILAGE

POLYAMIDE 11 PELLET

RILSAN® BMNO SG FILAGE is a polyamide 11 resin. It is produced from a renewable & sustainable source (castor oil). This natural grade is particularly suitable for textile applications.

Designation : ISO 16396 - PA11, M, C12-010

TYPE

PA11

MAIN APPLICATIONS

- Monofilament
- Industry - Distribution

DELIVERY FORM

- Pellets

TRANSFORMATION PROCESSES

- Filament extrusion
- Scattering, paste, double dot

RHEOLOGICAL PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Shrinkage, Normal (t+24h)	0.9	%	ISO 294-4
Shrinkage, Parallel (t+24h)	1.1	%	ISO 294-4
Melt volume flow rate (MVR), 235°C / 2.16 kg (455°F / 4.4 lb)	30	cm³/10min	ISO 1133

MECHANICAL PROPERTIES

PROPERTIES	DRY / COND VALUE*	UNIT	TEST STANDARD
Hardness, Shore D, 15 s	- / 68		ISO 868
Charpy unnotched impact strength, 23°C (73°F)	- / No Break		ISO 179 1eU
Charpy unnotched impact strength, -30°C (-22°F)	- / No Break		ISO 179 1eU
Nominal strain at break, 23°C (73°F), 50 mm/min	- / > 50	%	ISO 527-1/-2
Yield strain, 23°C (73°F), 50 mm/min	- / 5	%	ISO 527-1/-2
Yield stress, 23°C (73°F), 50 mm/min	- / 41	MPa	ISO 527-1/-2
Tensile modulus, 23°C (73°F), 1 mm/min	1280 / 1280	MPa	ISO 527-1/-2
Charpy notched impact strength, 23°C (73°F)	- / 8.3	kJ/m2	ISO 179 1eA
Charpy notched impact strength, -30°C (-22°F)	- / 10.5	kJ/m2	ISO 179 1eA
Flexural modulus, 23°C (73°F)	- / 1140	MPa	ISO 178

*DRY: Dry As Molded (DAM) if pellet / Dry if powder.
COND: Conditionned.

THERMAL PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Melting temperature, 10°C/min	189	°C	ISO 11357-1/-3

RILSAN® BMNO SG FILAGE

OTHER PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Bio-based carbon content, Measured	98	%	ASTM D6866
Water absorption, 23°C (73°F), immersion, equilibrium	1.9	%	ISO 62
Specific gravity, 23°C (73°F)	1.03	g/cm ³	ISO 1183-1

PACKAGING

Available packaging:

- 25 kg / 55 lb bags

SHELF LIFE

Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

PROCESSING CONDITIONS:

- Typical melt temperature (Min / Recommended / Max) - Injection Molding: 210°C / 230°C / 260°C (410°F / 445°F / 500°F)
- Typical mold temperature - Injection molding: 20-60°C (70-140°F)
- Drying time and temperature: 80-90°C (175-195°F) / 4-6 hours

SPECIAL CHARACTERISTICS

- Bio-based
- Low oligomers