

TECHNICAL DATA SHEET

RILSAN® BESNO 400 TL NL

POLYAMIDE 11 PELLET

RILSAN® BESNO P400 TL NL is a polyamide 11 compound. It is produced from a renewable & sustainable source (castor oil). This plasticized natural grade and designed for tube extrusion.

Designation : ISO 16396 - PA11-IP, EG1HL, C22-005

TYPE

PA11

MAIN APPLICATIONS

- Industry - Others

DELIVERY FORM

- Pellets

TRANSFORMATION PROCESSES

- Extrusion - General
- Tube Extrusion

ADDITIVES

- Heat Stabilized
- Light Stabilized

MECHANICAL PROPERTIES

PROPERTIES	DRY / COND VALUE*	UNIT	TEST STANDARD
Hardness, Shore D, 15 s	- / 49		ISO 868
Charpy unnotched impact strength, 23°C (73°F)	- / No Break		ISO 179 1eU
Charpy unnotched impact strength, -30°C (-22°F)	- / No Break		ISO 179 1eU
Tensile modulus, 23°C (73°F), 1 mm/min	- / 190	MPa	ISO 527-1/-2
Charpy notched impact strength, 23°C (73°F)	No Break / No Break		ISO 179 1eA
Charpy notched impact strength, -30°C (-22°F)	- / 15	kJ/m2	ISO 179 1eA

*DRY: Dry As Molded (DAM) if pellet / Dry if powder.
COND: Conditionned.

THERMAL PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Melting temperature, 10°C/min	182	°C	ISO 11357-1/-3

OTHER PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Specific gravity, 23°C (73°F)	1	g/cm³	ISO 1183-1

PACKAGING

Available packaging:

- 550 kg rigid containers

RILSAN® BESNO 400 TL NL

SHELF LIFE

Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

PROCESSING CONDITIONS:

- Typical melt temperature (Min / Recommended / Max) - Injection Molding: 230°C / 250°C / 270°C (445°F / 480°F / 520°F)
- Typical mold temperature - Injection molding: 20-60°C (70-140°F)
- Drying time and temperature: 80-90°C (175-195°F) / 4-6 hours

SPECIAL CHARACTERISTICS

- Bio-based
- Low oligomers