

RILSAN® BESNO P40 TLO

PA11-P, EHL, 22-003

Rilsan® BESNO P40 TLO resin is a polyamide 11 produced from a renewable source. This natural grade is plasticized and designed for extrusion. This grade contains a low amount of oligomers.

The percentage of renewable carbon according to ASTM D 6866 (calculated) is **>85%**.

PROPERTIES	DRY / COND	UNIT	TEST STANDARD
MECHANICAL PROPERTIES			
Tensile Modulus	- / 310	MPa	ISO 527-1/-2
	- /	psi	
Yield stress	45000 - / 26	MPa	ISO 527-1/-2
	- / 3770	psi	
Yield strain	- / 46	%	ISO 527-1/-2
Nominal Strain at Break	- / >50	%	ISO 527-1/-2
Shore D Hardness	60 / *	-	ISO 868
Charpy Impact Strength, +23°C	- / No Break	kJ/m²	ISO 179/1eU
Charpy Impact Strength, -30°C	- / No Break	kJ/m²	ISO 179/1eU
Charpy Notched Impact Strength, +23°C	- / No Break	kJ/m²	ISO 179/1eA
Charpy Notched Impact Strength, -30°C	- / 6	kJ/m²	ISO 179/1eA
	- / 2.85	ftlb/in²	
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	182 / *	°C	ISO 11357-1/-3
OTHER PROPERTIES			
Density	1040 / 1040	kg/m³	ISO 1183
	1.04 / 1.04	g/cm³	
%Bio-Based	85	-	ASTM D6866

MAIN APPLICATIONS:

- Fluid transportation
- Tubing for use in motor vehicle
- Clean hose for offshore umbilicals

PACKAGING:

This grade is delivered dried in sealed packaging (25 kg bags, 550 kg rigid containers) ready to be processed.

SHELF LIFE:

Two years from the delivery. For any use above this limit, please refer to our technical services.

RILSAN® BESNO P40 TLO

Processing conditions:

- Typical melt temperature (Min / Recommended / Max) : 230°C / 250°C / 287°C.

- Drying time and temperature (only necessary for bags opened for more than two hours) : 4-8 hours at 80-90°C.

PROCESSING	
Profile Extrusion, Other Extrusion	
DELIVERY FORM	
Pellets	
ADDITIVES	
Lubricants, Plasticizer	
SPECIAL CHARACTERISTICS	
Bio-Based, Heat Stabilized, Light Stabilized	
REGIONAL AVAILABILITY	
North America, Europe, Asia Pacific, South and Central America, Near East/Africa	