## +188-1699-6168 (ShangHai) +852-6957-5415 (HongKong) R ILSAN **FINE POWDERS** ES BLUE 7413 MAC

## **Rilsan® 7413 Blue MAC Electrostatic Spray Powder**

Rilsan® electrostatic spray powders are thermoplastic polyamides obtained from renewable resources.

Outstanding characteristics: abrasion resistance, corrosion resistance, impact resistance, sound reduction, flexibility, low coefficient of friction.

+135-3858-6433 (GuangDong)

PROPERTIES	VALUE	UNIT	TEST STANDARD
POWDER PROPERTIES			
Color	Blue	-	-
Particle Size Distribution, Median Size	≥30	μm	ISO 13320
	≥0.00118	in	
1elting Temperature 18	183 - 188	°C	ISO 1218
	361 - 370	°F	
Non Tapped Density	0.44	-	ISO 1068
Tapped Density	0.62	-	ISO 1068
POWDER COATING PROPERTIES			
Covering Efficiency , 120µm	0.14	kg/m²	-
Specific Gravity of Coating, 20°C	1.18	-	ISO 1183
Persoz Hardness	270	-	ISO 1522
Water Absorption, 24h	≤1	%	ISO 62-1
Abrasion Resistance, Wheel CS 17, load 1 kg, 1000 cycles	17	mg	ISO 9352

## MAIN APPLICATIONS:

- coating of wire goods and piping components exposed to high weathering or corrosive environments
- Rilsan® electrostatic spray powders ٠ are designed to coat metal substrates via a charged powder spraying gun. MAC grades exhibit improved weathering capabilities for outdoor applications
- of salt spray testing (ISO 9227)
- 5 year shelf life from date of manufacture

- · coating of machinery exposed to high · coating of springs for sound reduction abrasion such as spline shafts
- Additional info

- · Smooth texture with a glossy appearance
- Good adhesion after over 2000 hours Only 20% fine particles < 20 µm (ISO Only 1% coarse particles > 100 µm 13320)
  - · Available in 20 kg bags
- (ISO 13320)





PROCESSING
Coating, Electrostatic Spray
DELIVERY FORM
Powder

