

RILSAN®

FINE POWDERS

T GREY 7017 BHV RX

+135-3858-6433 (GuangDong)
+188-1699-6168 (ShangHai)
+852-6957-5415 (HongKong)

Rilsan® 7017 Grey BHV RX FB Fluid Bed Powder

RILSAN® fine powders are specialty polyamide powders obtained from renewable resources. RILSAN® T range is designed for coating metal parts using the fluidized bed dip coating process. They provide superior protection against wear, impact, corrosion, chemicals as well as graffiti. Please consult Arkema literature for application method and recommendations

PROPERTIES	VALUE	UNIT	TEST STANDARD
POWDER PROPERTIES			
Color	Grey	-	-
Particle Size Distribution, ≤ 40µm	8	%	ISO 13320
Particle Size Distribution, ≥ 254µm	10	%	ISO 13320
Particle Size Distribution, Median Size	100 - 130	µm	ISO 13320
	0.00394 - 0.00512	in	
Melting Temperature	183 - 188	°C	ISO 1218
	361 - 370	°F	
Vicat Point	181	°C	ISO 306
	358	°F	
Non Tapped Density	0.52	-	ISO 1068
Tapped Density	0.62	-	ISO 1068
Fluidized Density	0.5	-	-
POWDER COATING PROPERTIES			
Recommended Coating Thickness	≥300	µm	-
	≥0.0118	in	
Covering Efficiency , 300µm	0.36	kg/m²	-
Specific Gravity of Coating, 20°C	1.05	-	ISO 1183
Persoz Hardness	240	-	ISO 1522
Shore D Hardness	70	-	ISO 868
Water Absorption, 24h	≤1	%	ISO 62-1
Abrasion Resistance, Wheel CS 17, load 1 kg, 1000 cycles	15	mg	ISO 9352
Impact Resistance	≥2	J	ASTM G14
	≥17.7	in-lb	
Salt spray test according to surface preparation recommended by ARKEMA	Good adhesion after 2000 hours	-	ISO 9227

MAIN APPLICATIONS

- Metal Coating
- Roller Industry

PACKAGING

This grade is delivered in 20kg bags.

ARKEMA

RILSAN®

FINE POWDERS

T GREY 7017 BHV RX

SHELF LIFE

Five years from the date of delivery. For any use after this limit, please refer to our technical services.

PROCESSING	
Coating, Fluidized Bed Dipping	
DELIVERY FORM	
Powder	