# RILSAN®

#### TECHNICAL DATA SHEET

### **RILSAN® PA11 D40 NAT**

#### **POLYAMIDE 11 POWDER**

RILSAN<sup>®</sup> D40 NAT is a polyamide 11 powder obtained from renewable resources with an average diameter of 27 - 31 μm. RILSAN<sup>®</sup> D is a range of high performance fine polyamide powders used as multifunctional additives in coatings and varnishes.

The introduction of RILSAN® polyamide powders in formulations is easy thanks to their good dispersion capacity, their reduced Impact on rheology and their low density.

RILSAN® polyamide powders are surface modifiers, specifically designed for texture creation.

Abrasion, scratch, impact resistances and flexibility of coatings, inks and varnishes can be significantly improved using RILSAN® polyamide powders.

| <b>TYPE</b><br>PA11  | • Powder  |
|--|---|
| MAIN APPLICATIONS <ul> <li>Coating Additives - Others</li> <li>Coating Additives - Wood</li> <li>Coating Additives - Flooring</li> <li>Coating Additives - Coil Coating</li> </ul> | <ul> <li>TRANSFORMATION PROCESSES</li> <li>Formulation ingredients</li> <li>ADDITIVES</li> <li>Heat Stabilized</li> </ul> |

#### **THERMAL PROPERTIES**

| PROPERTIES                                 | VALUE   | UNIT | TEST STANDARD  |
|--|---------|------|----------------|
| Vicat softening temperature, 50N at 50°C/h | 160     | °C   | ISO 306        |
| Melting temperature, 10°C/min              | 183-188 | °C   | ISO 11357-1/-3 |

#### **ELECTRICAL PROPERTIES**

| PROPERTIES                                     | DRY / COND VALUE* | UNIT   | TEST STANDARD |
|--|-------------------|--------|---------------|
| Surface resistivity, 23°C (73°F)               | - / 1.0E+14       | Ohm/sq | IEC 62631-3-2 |
| Volumic (transversal) resistivity, 23°C (73°F) | - / 1.0E+12       | Ohm.m  | IEC 62631-3-1 |
| Dielectric Strength, 23°C (73°F)               | - / 30            | kV/mm  | IEC 60243-1   |

\*DRY: Dry As Molded (DAM) if pellet / Dry if powder.

COND: Conditionned.

#### **OTHER PROPERTIES**

| PROPERTIES  | VALUE | UNIT  | TEST STANDARD |
|---|-------|-------|---------------|
| Median particles (D50)                              | 27-31 | μm    | ISO 13319     |
| Water absorption, Saturated in water at 23°C (73°F) | 1.9   | %     | ISO 62        |
| Apparent density, Non compacted                     | 0.37  |       | ISO 1068      |
| Specific gravity of coating, 20°C (68°F)            | 1.04  | g/cm³ | ISO 1183-1    |

#### PACKAGING

Available packaging:

• 20 kg / 44 lb bags





## **RILSAN® PA11 D40 NAT**

#### SHELF LIFE

Five years shelf life from date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

#### **SPECIAL CHARACTERISTICS**

• Bio-based

