

## TECHNICAL DATA SHEET

# RILSAN® PA11 ESY BLACK 7298

## POLYAMIDE 11 POWDER

RILSAN® fine powders are specialty polyamide powders obtained from renewable resources. RILSAN® ESY range is designed for coating metal parts using the electrostatic spraying process. They provide superior protection against wear, impact, corrosion, chemicals as well as graffiti. Please consult Arkema literature for application method and recommendations.

### TYPE

PA11

### MAIN APPLICATIONS

- Water Fluid Coating - Water Accessories
- Oil And Gas - Energy Pipe Coating
- Automotive/Truck - Automotive Coating

### DELIVERY FORM

- Powder

### TRANSFORMATION PROCESSES

- Electrostatic spraying

### ADDITIVES

- Heat Stabilized

## MECHANICAL PROPERTIES

PROPERTIES	DRY / COND VALUE*	UNIT	TEST STANDARD
Hardness, Shore D, 23°C (73°F)	- / 72		ISO 868
Hardness, Persoz, 23°C (73°F)	- / 270		ISO 1522
Taber abrasion, Wheel CS 17, load 1 kg, 1000 cycles	- / 17	mg	ISO 9352

\*DRY: Dry As Molded (DAM) if pellet / Dry if powder.  
COND: Conditioned.

## THERMAL PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Melting temperature, 10°C/min	183-188	°C	ISO 11357-1/-3
Vicat softening temperature, 50N at 50°C/h	181	°C	ISO 306

# RILSAN® PA11 ESY BLACK 7298

## OTHER PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Covering efficiency (100 µm)	0.20	kg/m <sup>2</sup>	Internal Arkema
Water absorption, 24h	≤ 1	%	ISO 62
Median particles (D50)	30	µm	ISO 13320
Approximate RAL number	9005		
Salt spray test	Good adhesion after 2000 hours		ISO 9227
Specific gravity of coating, 20°C (68°F)	1.19	g/cm <sup>3</sup>	ISO 1183-1
Apparent density, Non compacted	0.44		ISO 1068
Apparent density, Compacted	0.62		ISO 1068
Particle Size Distribution (PSD) (Fine particles < 20 µm)	20	%	ISO 13320
Particle Size Distribution (PSD) (Coarse particles > 100 µm)	1	%	ISO 13320

## PACKAGING

Available packaging:

- 20 kg / 44 lb bags

## SHELF LIFE

Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

## SPECIAL CHARACTERISTICS

- Bio-based