

## TECHNICAL DATA SHEET

# RILSAN® PA11 T WHITE 1488

## POLYAMIDE 11 POWDER

RILSAN® fine powders are specialty polyamide powders obtained from renewable resources. RILSAN® T range is designed for coating metal parts using the fluidized bed dip coating process. They provide superior protection against wear, impact, corrosion, chemicals as well as graffiti. Please consult Arkema literature for application method and recommendations.

### TYPE

PA11

### MAIN APPLICATIONS

- Water Fluid Coating - Piping Systems
- Powder Coating- Wire Goods
- Automotive/Truck - Automotive Coating

### DELIVERY FORM

- Powder

### TRANSFORMATION PROCESSES

- Fluidized Bed Dipping

### ADDITIVES

- Heat Stabilized

## MECHANICAL PROPERTIES

PROPERTIES	DRY / COND VALUE*	UNIT	TEST STANDARD
Hardness, Persoz, 23°C (73°F)	- / 240		ISO 1522
Hardness, Shore D, 23°C (73°F)	- / 79		ISO 868
Coating impact, 23°C (73°F)	- / ≥ 2	J	ASTM G14
Taber abrasion, Wheel CS 17, load 1 kg, 1000 cycles	- / 13	mg	ISO 9352

\*DRY: Dry As Molded (DAM) if pellet / Dry if powder.  
COND: Conditionned.

## THERMAL PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Melting temperature, 10°C/min	183-188	°C	ISO 11357-1/-3
Vicat softening temperature, 50N at 50°C/h	181	°C	ISO 306

# RILSAN® PA11 T WHITE 1488

## OTHER PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Median particles (D50)	100-130	µm	ISO 13320
Apparent density, Non compacted	0.55		ISO 1068
Apparent density, Compacted	0.66		ISO 1068
Approximate RAL number	9010		
Covering efficiency (300 µm)	0.35	kg/m <sup>2</sup>	Internal Arkema
Particle Size Distribution (PSD), Fine particles (≤ 40 µm)	1	%	ISO 13320
Particle Size Distribution (PSD), Coarse particles (> 254 µm)	4	%	ISO 13320
Water absorption, 24h	≤ 1	%	ISO 62
Salt spray test	Good adhesion after 2000 hours		ISO 9227
Specific gravity of coating, 20°C (68°F)	1.17	g/cm <sup>3</sup>	ISO 1183-1

## PACKAGING

Available packaging:

- 25 kg / 55 lb bags

## SHELF LIFE

Five years shelf life from date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

## SPECIAL CHARACTERISTICS

- Bio-based