

# PEBAX® 7033 SA 01 MED

Polyether block amide Pebax® 7033 SA 01 MED is a thermoplastic elastomer made of flexible polyether and rigid polyamide. This grade offers the highest quality and it is specially designed to meet the stringent requirements of the medical applications such as minimally invasive devices. Pebax® 7033 SA 01 MED also offers an excellent combination of properties such as: kink resistance, low friction coefficient and superior dynamic response. Upon request, letters regarding USP Class VI compliance can be provided.

## MAIN CHARACTERISTICS

Property	Typical Value	Unit	Test Method
<b>Density</b>	<b>1.01</b>	g/cm <sup>3</sup>	ISO 1183
<b>Water Absorption at Equilibrium</b> At 20°C and 50 % R.H.	<b>0.7</b>	%	ISO 62
<b>Water Absorption</b> At 23°C and 24 h in water	<b>1.1</b>	%	
<b>Melting Point</b>	<b>172</b>	°C	ISO 11357
<b>Vicat Point</b> Under 1 daN	<b>164</b>	°C	ISO 306
<b>Shrinkage (after 24 h, 4 mm, mold at 40°C)</b> // ⊥	<b>1.2</b> <b>1.5</b>	% %	Internal method
<b>Hardness (*)</b> Instantaneous After 15 s	<b>69</b> <b>61</b>	Shore D Shore D	
<b>Tensile Test (*)</b> Stress at Break Strain at Break	<b>54</b> <b>&gt;350</b>	MPa %	ISO 527
<b>Flexural Modulus (*)</b>	<b>390</b>	MPa	ISO 178
<b>Charpy Impact (*)</b> Unnotched 23°C Unnotched -30°C V-notched 23°C V-notched -30°C	<b>No break</b> <b>No break</b> <b>120 (p)</b> <b>20 (c)</b>	<b>kJ/m<sup>2</sup></b> <b>kJ/m<sup>2</sup></b> <b>kJ/m<sup>2</sup></b> <b>kJ/m<sup>2</sup></b>	ISO 179

(\*) Samples conditioned 15 days at 23°C - 50 % R.H.

(p) = Partial Break; (c) = Complete Break

# PEBAX® 7033 SA 01 MED

## MAIN APPLICATIONS

- Tubings like angiography and angioplasty catheters.
- Flexible injected parts.

## PROCESSING CONDITIONS

Conditions	Typical values
<b>Extrusion</b> Melt Temperature (Min / Recommended / Max)	220°C / 235°C / 250°C
<b>Injection</b> Melt Temperature (Min / Recommended / Max)	230°C / 260°C / 290°C
<b>Mold</b> Temperature	25 – 60°C
<b>Drying (only necessary for bags opened for more than two hours)</b> Time Temperature	5 - 7 hours 70 - 80°C

## PACKAGING

This grade is delivered dried in sealed packaging (20 kg bags) ready to be processed.