



4033 SD 01

Polyether block amide **PEBAX® 4033 SD 01** is a thermoplastic elastomer made of flexible polyether and rigid polyamide. This SD grade is heat and UV stabilized and contains mould release additive.

Main Characteristics	Value	Unit	Test Method
Density	1.00	g/cm ³	ISO 1183
Water Absorption at Equilibrium at 20°C and 50 % RH	0.5	%	ISO 62
Water Absorption at Saturation 24 h in water at 23°C	1.2	%	
Melting Point	160	°C	ISO 11357
Vicat Point Under 1 daN	131	°C	ISO 306
Hardness Shore (*) Instantaneous	42	Shore D	ISO 868
After 15 s	35	Shore D	
Tensile Test (*) Stress at Break	40	MPa	ASTM D 638
Strain at Break	>450	%	
Flexural Modulus (*)	77	MPa	ISO 178
Charpy Impact unnotched 23°C	No break	kJ/m ²	ISO 179
unnotched -30°C	No break	kJ/m ²	
V-notched 23°C	No break	kJ/m ²	
V-notched -30°C	No break	kJ/m ²	

(*) Samples conditioned 15 days at 23°C - 50 % R.H.

Processing Conditions	Typical Values
Drying (*): Time / Temperature	4-6 hours / 60-70°C
Injection Temperature: Min / Recommended / Max	200°C / 240°C / 270°C
Mold Temperature:	10-30°C

(*) Pebax® is delivered dried in sealed packaging ready to be processed. Drying is only necessary for bags opened for more than 2 hours.