

RILSAMID®

AESN BLACK P40 TL

ISO 16396 - PA12-P, EGHL, C22-004

Rilsamid® AESN BLACK P40 TL resin is a black plasticized grade designed for tube extrusion.

Rilsamid® AESN BLACK P40 TL resin falls into the PA12-PHL category according to DIN 73378.

PROPERTIES	DRY / COND	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Volume-Flow Rate	10 / *	cm³/10min	ISO 1133
Temperature	235 / *	°C	-
	455 / *	°F	
Load	5 / *	kg	-
	11 / *	lb	
MECHANICAL PROPERTIES			
Tensile Modulus	- / 445	MPa	ISO 527-1/-2
	- /	psi	
Yield stress	64500	MPa	ISO 527-1/-2
	- / 27	psi	
	- / 3920	psi	
Yield strain	- / 27	%	ISO 527-1/-2
Nominal Strain at Break	- / >50	%	ISO 527-1/-2
Shore D Hardness	62 / *	-	ISO 868
Charpy Impact Strength, +23°C	- / No Break	kJ/m²	ISO 179/1eU
Charpy Impact Strength, -30°C	- / No Break	kJ/m²	ISO 179/1eU
Charpy Notched Impact Strength, +23°C	- / No Break	kJ/m²	ISO 179/1eA
Charpy Notched Impact Strength, -30°C	- / 5	kJ/m²	ISO 179/1eA
	- / 2.38	ftlb/in²	
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	174 / *	°C	ISO 11357-1/-3
OTHER PROPERTIES			
Density	1030 / -	kg/m³	ISO 1183
	1.03 / -	g/cm³	

MAIN APPLICATIONS:

* Air brake.

* Tubing for use in motor vehicles.

RILSAMID[®]

AESN BLACK P40 TL

PACKAGING:

This grade is delivered dried in sealed packaging (25 kg bags) ready to be processed.

SHELF LIFE:

Two years from the date of delivery. for any use above this limit, please refer to our technical services.

Processing conditions, Extrusion:

- Typical Melt temperature (Min / Recommended / Max) : 210°C / 230°C / 260°C
- Drying time and temperature (only necessary for bags opened for more than two hours) : 4 - 8 hours at 80°C

PROCESSING Profile Extrusion, Other Extrusion	
DELIVERY FORM Pellets	
ADDITIVES Plasticizer	
SPECIAL CHARACTERISTICS Heat Stabilized, Light Stabilized	
REGIONAL AVAILABILITY North America, Europe, Asia Pacific, South and Central America, Near East/Africa	