

RILSAMID® MA 4411 BLACK

PA12, MHLR, 16-010

Rilsamid® MA 4411 BLACK resin is plasticized and designed for tube extrusion.

Rilsamid® MA 4411 BLACK resin falls into the PA12-HIPHL category according to DIN 73378 (PA12-HIP, EHL, 22-004).

PROPERTIES	DRY / COND	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Volume-Flow Rate	14 / *	cm ³ /10min	ISO 1133
Temperature	235 / *	°C	-
	455 / *	°F	-
Load	5 / *	kg	-
	11 / *	lb	-
MECHANICAL PROPERTIES			
Tensile Modulus	- / 470	MPa	ISO 527-1/-2
	- /	psi	
Yield stress	68200 - / 25	MPa	ISO 527-1/-2
	- / 3630	psi	
Yield strain	- / 23	%	ISO 527-1/-2
Nominal Strain at Break	- / >50	%	ISO 527-1/-2
Shore D Hardness	63 / *	-	ISO 868
Charpy Impact Strength, +23°C	- / No Break	kJ/m ²	ISO 179/1eU
Charpy Impact Strength, -30°C	- / No Break	kJ/m ²	ISO 179/1eU
Charpy Notched Impact Strength, +23°C	- / No Break	kJ/m ²	ISO 179/1eA
Charpy Notched Impact Strength, -30°C	- / 6	kJ/m ²	ISO 179/1eA
	- / 2.85	ftlb/in ²	
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	175 / *	°C	ISO 11357-1/-3
OTHER PROPERTIES			
Density	1030 / -	kg/m ³	ISO 1183
	1.03 / -	g/cm ³	

RILSAMID[®]

MA 4411 BLACK

PROCESSING Profile Extrusion, Other Extrusion	
DELIVERY FORM Pellets	
ADDITIVES Plasticizer	
SPECIAL CHARACTERISTICS Heat Stabilized, Light Stabilized	
REGIONAL AVAILABILITY North America, Europe, Asia Pacific, South and Central America, Near East/Africa	