

TECHNICAL DATA SHEET

RILSAMID® AESNO 14 TL

POLYAMIDE 12 PELLET

RILSAMID® AESNO 14 TL is a polyamide 12 compound. This natural grade is designed for tube extrusion and specially adapted to applications in which transparency is required.

Designation : ISO 16396 - PA12, EG1HL, C22-010

TYPE

PA12

MAIN APPLICATIONS

- Winter Sports - Ski

DELIVERY FORM

- Pellets

TRANSFORMATION PROCESSES

- Extrusion - General
- Sheet Extrusion
- Tube Extrusion

ADDITIVES

- Heat Stabilized
- Light Stabilized

RHEOLOGICAL PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Melt volume flow rate (MVR), 235°C / 5 kg (455°F / 11 lb)	2.1	cm³/10min	ISO 1133

MECHANICAL PROPERTIES

PROPERTIES	DRY / COND VALUE*	UNIT	TEST STANDARD
Tensile modulus, 23°C (73°F), 1 mm/min	1125 / 1125	MPa	ISO 527-1/-2
Yield strain, 23°C (73°F), 50 mm/min	- / 11	%	ISO 527-1/-2
Charpy notched impact strength, 23°C (73°F)	- / 63	kJ/m2	ISO 179 1eA
Charpy notched impact strength, -30°C (-22°F)	- / 11	kJ/m2	ISO 179 1eA
Charpy unnotched impact strength, 23°C (73°F)	No Break / No Break		ISO 179 1eU
Charpy unnotched impact strength, -30°C (-22°F)	No Break / No Break		ISO 179 1eU
Nominal strain at break, 23°C (73°F), 50 mm/min	- / > 50	%	ISO 527-1/-2
Yield stress, 23°C (73°F), 50 mm/min	- / 34	MPa	ISO 527-1/-2
Flexural modulus, 23°C (73°F)	- / 910	MPa	ISO 178

*DRY: Dry As Molded (DAM) if pellet / Dry if powder.
COND: Conditionned.

THERMAL PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Melting temperature, 10°C/min	178	°C	ISO 11357-1/-3

RILSAMID® AESNO 14 TL

OTHER PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Specific gravity, 23°C (73°F)	1.01	g/cm ³	ISO 1183-1

PACKAGING

Available packaging:

- 550 kg rigid containers

SHELF LIFE

Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

PROCESSING CONDITIONS:

- Typical melt temperature (Min / Recommended / Max) - Injection Molding: 230°C / 250°C / 270°C (445°F / 480°F / 520°F)
- Typical mold temperature - Injection molding: 20-60°C (70-140°F)
- Drying time and temperature: 80-90°C (175-195°F) / 4-6 hours

SPECIAL CHARACTERISTICS

- Transparent

DIAGRAMS

