

TECHNICAL DATA SHEET

PEBAX® RNEW® 40R53 SP 01

POLYETHER BLOCK AMIDE PELLET

PEBAX® RNEW® 40R53 SP 01 is a polyether block amide, a thermoplastic elastomer made of flexible polyether and rigid polyamide. It is partially produced from a renewable & sustainable source (castor oil). This SP grade is heat & UV stabilized. It is used in sport and consumer applications.

TYPE

PEBA

MAIN APPLICATIONS

- Footwear - Outsole/Components
- Industry - Others
- Industry - Distribution
- Extrusion - Industrial
- Extrusion - Consumer Goods

DELIVERY FORM

- Pellets

TRANSFORMATION PROCESSES

- Extrusion - General
- Film Extrusion
- Injection Molding
- Tube Extrusion

ADDITIVES

- Heat Stabilized
- Light Stabilized

RHEOLOGICAL PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Shrinkage, Parallel (t+24h)	0.5	%	ISO 294-4
Shrinkage, Normal (t+24h)	1.2	%	ISO 294-4

MECHANICAL PROPERTIES

PROPERTIES	DRY / COND VALUE*	UNIT	TEST STANDARD
Flexural modulus, 23°C (73°F)	- / 75	MPa	ISO 178
Tensile modulus, 23°C (73°F), 1 mm/min	- / 75	MPa	ISO 527-1/-2
Stress at 50% strain, 23°C (73°F), 50 mm/min	- / 8.2	MPa	ISO 527-1/-2
Nominal strain at break, 23°C (73°F), 50 mm/min	- / > 400	%	ISO 527-1/-2
Stress at break, 23°C (73°F), 50 mm/min	- / 45	MPa	ISO 527-1/-2
Hardness, Shore D, 15 s	- / 39		ISO 868
Charpy unnotched impact strength, 23°C (73°F)	No Break / No Break		ISO 179 1eU
Charpy unnotched impact strength, -30°C (-22°F)	No Break / No Break		ISO 179 1eU
Charpy notched impact strength, 23°C (73°F)	No Break / No Break		ISO 179 1eA
Charpy notched impact strength, -30°C (-22°F)	No Break / No Break		ISO 179 1eA

*DRY: Dry As Molded (DAM) if pellet / Dry if powder.
COND: Conditionned.

THERMAL PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Melting temperature, 10°C/min	148	°C	ISO 11357-1/-3

PEBAX® RNEW® 40R53 SP 01

OTHER PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Water absorption, 23°C (73°F), immersion, equilibrium	1.4	%	ISO 62
Bio-based carbon content, Measured	45	%	ASTM D6866
Moisture absorption, At equilibrium at 23°C (73°F) / 50%HR	0.5	%	ISO 62
Specific gravity, 23°C (73°F)	1.03	g/cm ³	ISO 1183-1

PACKAGING

Available packaging:

- 25 kg / 55 lb bags

SHELF LIFE

Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

PROCESSING CONDITIONS:

- Typical melt temperature (Min / Recommended / Max) - Injection Molding: 210°C / 240°C / 270°C (410°F / 430°F / 520°F)
- Typical mold temperature - Injection molding: 10-30°C (50-90°F)
- Drying time and temperature: 60-70°C (140-160°F) / 4-8 hours

SPECIAL CHARACTERISTICS

- Bio-based

REGIONAL AVAILABILITY

Asia Pacific, Europe, Latin America and the Caribbean, Middle East, Northern America

DIAGRAMS

