

KEPSTAN[®] 8010C30

KEPSTAN® PEKK resin is a high performance thermoplastic material, based on PolyEtherKetoneKetone (PEKK) highly stable chemical backbone. Its semi crystalline structure in solid state offers an outstanding combination of mechanical and thermal strength together with chemical and fire resistance.

KEPSTAN® 8010C30 is a carbon fiber reinforced compound, based on the 8000 series of KEPSTAN® resins. This series offers the highest glass transition temperature and the highest crystallinity, leading to the best tensile and compression strengths among the different series of KEPSTAN® PEKK copolymers.

KEPSTAN® 8010C30 is a low flow grade, suitable for extrusion, compression and injection molding.

KEPSTAN® 8010C30 is available in pellet form, and standard packaging is 10 kg boxes.

PROPERTIES	VALUE	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Volume-Flow Rate	18	cm ³ /10min	ISO 1133
Temperature	380	°C	-
	716	°F	
Load	5	kg	-
	11	lb	
MECHANICAL PROPERTIES			
Tensile Modulus	24300	MPa	ISO 527-1/-2
	3.52E6	psi	
Charpy Impact Strength, +23°C	37	kJ/m²	ISO 179/1eU
	17.6	ftlb/in ²	
Charpy Notched Impact Strength, +23°C	6	kJ/m²	ISO 179/1eA
	2.85	ftlb/in ²	
OTHER PROPERTIES			
Density	1390	kg/m³	ISO 1183
	1.39	g/cm ³	

Drying temperature and time: 150°C for 3 to 4 hours or 120°C for 6 to 8 hours

Processing temperature: 375 – 385°C

Temperature settings - Injection: Rear 350°C / Center 375°C / Front 375°C / Nozzle 385°C Mold temperature (to facilitate filling of the cavity and polymer crystallization): 230 - 240°C Temperature settings - Extrusion: Zones 1/2/3/4: 355°C/ 370°C/ 385°C/ 385°C Die: 370°C



KEPSTAN[®] 8010C30

PROCESSING Injection Molding, Profile Extrusion DELIVERY FORM Pellets REGIONAL AVAILABILITY North America, Europe, Asia Pacific, South and Central America, Near East/Africa

