

KYNAR® ADHEFLON ASP 720

Kynar® resins are fluorinated thermoplastic homopolymers.

This product is used for the co-extrusion of Rilsan® polyamides and Kynar® PVDF resins for the preparation of multilayer tubing or film.

PROPERTIES	VALUE	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Volume-Flow Rate	12.5	cm³/10min	ISO 1133
Temperature	230	°C	-
	446	°F	-
Load	10	kg	-
	22	lb	-
Melt Viscosity, 230°C, 100 s-1	1.6	kPoise	ASTM D3835
MECHANICAL PROPERTIES			
Elongation at Break, 73 °F	≥100	%	ASTM D638
THERMAL PROPERTIES			
Melting Point, 73 °F	166	°C	ASTM D3418
OTHER PROPERTIES			
Density	1270	kg/m³	ISO 1183
	1.27	g/cm³	

PROCESSING Film Extrusion, Sheet Extrusion, Other Extrusion	
DELIVERY FORM Pellets	
REGIONAL AVAILABILITY North America, Europe, Asia Pacific, South and Central America, Near East/Africa	