

KYNAR FLEX[®]

TECHNICAL DATA SHEET

KYNAR FLEX[®] PPA 8600

FLUORINATED COPOLYMER PELLET

KYNAR FLEX[®] resins are fluorinated thermoplastic copolymers.
KYNAR FLEX[®] PPA 8600 resin is specially designed pellet used as a polymer process aid (PPA) for polyolefins.
The use of KYNAR FLEX[®] PPA 8600 resin at 200 - 1000 ppm levels reduces extruder pressure, improves surface finish, reduces die build up, and improves gauge control.
This product is also available on a powder form as KYNAR FLEX[®] PPA 8601 resin.

TYPE

PVDF

MAIN APPLICATIONS

- Polymer Processing Aid

DELIVERY FORM

- Pellets

THERMAL PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Glass transition temperature, 10°C/min	-40	°C	ISO 11357-1/-2
Melting temperature, 10°C/min	165	°C	ISO 11357-1/-3

PACKAGING

Available packaging:

- 25 kg / 55 lb bags

SPECIAL CHARACTERISTICS

- Flame & smoke