

KYNAR FLEX®

TECHNICAL DATA SHEET

KYNAR FLEX® 2850-04

FLUORINATED COPOLYMER PELLET

KYNAR FLEX® resins are fluorinated thermoplastic copolymers. Outstanding characteristics: chemical resistance, imperviousness to UV, high barrier properties, high purity, good mechanical and thermomechanical properties. This product is NSF/ANSI/CAN 61 certified. KYNAR FLEX® 2850-04 resin is a standard grade of granules less flexible than the grade KYNAR FLEX® 2800-20 resin with a higher melting point. It has a UL RTI temperature rating of 140 degrees C.

TYPE

PVDF

MAIN APPLICATIONS

- Molding

DELIVERY FORM

- Pellets

RHEOLOGICAL PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Melt viscosity, 230°C (445°F) at 100 s-1	4 - 8	kPo	ASTM D3835
Melt flow index (MFR), 235°C / 5 kg (455°F / 11 lb)	4 - 25	g/10min	ASTM D1238
Melt volume flow rate (MVR)	15	cm³/10min	ISO 1133

MECHANICAL PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Yield stress, 23°C (73°F)	31 - 41.4	MPa	ASTM D638
Yield strain, 23°C (73°F), 50 mm/min	10	%	ISO 527-1/-2
Stress at break, 23°C (73°F)	27.6 - 48.3	MPa	ASTM D638
Nominal strain at break, 23°C (73°F), 50 mm/min	>50	%	ISO 527-1/-2
Compression strength, 23°C (73°F)	41.4 - 58.6	MPa	ASTM D695
Izod impact unnotched strength, 23°C (73°F)	No Break		ASTM D256
Izod impact notched strength, 23°C (73°F)	0.107 - 0.427	J/m	ASTM D256
Charpy notched impact strength, 23°C (73°F)	8	kJ/m2	ISO 179 1eA
Hardness, Shore D	70 - 75		ASTM D2240
Flexural modulus, 23°C (73°F)	1030 - 1240	MPa	ASTM D790
Tensile modulus, 23°C (73°F)	1300	MPa	ASTM D638
Coefficient of friction dynamic vs steel, 23°C (73°F)	0.19		ASTM D1895
Coefficient of friction static vs steel, 23°C (73°F)	0.26		ASTM D1894
Abrasion resistance, Wheel CS 17, load 1 kg, 1000 cycles	6 - 9	mg	ASTM G195-13A

KYNAR FLEX® 2850-04

THERMAL PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Glass transition temperature, 10°C/min	-40	°C	ISO 11357-1/-2
Limiting oxygen index (LOI)	43	%	ASTM D2863
Yellow card available	yes		
Coefficient of linear thermal expansion, 23°C (73°F)	126 - 185	10E-6 / °K	ASTM D696
Specific heat temperature, 23°C (73°F)	745 - 958		ISO 11357-1/-2
Heat deflection temperature, 1.8 MPa	46	°C	ISO 75-1/-2
Heat deflection temperature, 1.8 MPa, 138°C/h	37.8 - 55	°C	ASTM D648
Heat deflection temperature, 0.45 MPa, 138°C/h	60-75	°C	ASTM D648
Thermal conductivity	0.144 - 0.18	W/m-K	ASTM D433
Melting temperature, 10°C/min	157	°C	ISO 11357-1/-3

ELECTRICAL PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Dielectric constant, 1kHz	3.5 - 10.2		ASTM D150
Dielectric strength, 23°C (73,4°F)	1.3 - 1.6	kV/mm	ASTM D149
Volumic (transversal) resistivity, DC, 20°C (68°F)/50%RH	2.0E+12	ohm*m	ASTM D257
Relative thermal index	140		
Dissipation factor	0.01 - 0.22		ASTM D150

OTHER PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Specific gravity, 23°C (73°F)	1.77 - 1.8	g/cm³	
Water absorption, Saturated in water at 23°C (73°F)	0.04	%	ASTM D570

PACKAGING

Available packaging:

- 25 kg / 55 lb rigid container
- 680 kg /1500 lb rigid container

SPECIAL CHARACTERISTICS

- Flame & smoke