

KYNAR FLEX®

2850 PC

Kynar Flex® resins are fluorinated thermoplastic copolymers.

Kynar Flex® 2850 PC resin powder coating is a semi-crystalline copolymer of vinylidene fluoride and hexafluoropropylene.

It has a special particle size making it ideal for spray applied powder coating on metal substrates for abrasion and corrosion protection

PROPERTIES	VALUE	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Volume-Flow Rate	7.5	cm³/10min	ISO 1133
Temperature	230	°C	-
	446	°F	-
Load	3.8	kg	-
	8.38	lb	-
Melt Flow Rate	8 - 25	g/10min	ASTM D1238
Temperature	230	°C	-
Load	3.8	kg	-
Melt Viscosity, 230°C, 100 s-1	4 - 8	kPoise	ASTM D3835
MECHANICAL PROPERTIES			
Tensile Modulus, 73 °F	1030 - 1520	MPa	ASTM D638
	150000 - 220000	psi	
Yield stress	35	MPa	ISO 527-1/-2
	5080	psi	
Tensile Strength at Yield, 73 °F	31 - 41.4	MPa	ASTM D638
	4500 - 6000	psi	
Yield strain	10	%	ISO 527-1/-2
Elongation at Yield, 73 °F	5 - 15	%	ASTM D638
Nominal Strain at Break	>50	%	ISO 527-1/-2
Tensile Strength at Break, 73 °F	27.6 - 48.3	MPa	ASTM D638
	4000 - 7000	psi	
Elongation at Break, 73 °F	30 - 200	%	ASTM D638
Taber Abrasion, CS 17 1000g:pad	6 - 9	mg/1000 cycles	ASTM-G195-13A
Hardness, Shore D, 73 °F	70 - 75	-	ASTM D2240
Flexural Modulus, 73 °F	1030 - 1240	MPa	ASTM D790
	150000 - 180000	psi	
Flexural Stength @ 5% Strain, 73 °F	20.7 - 27.6	MPa	ASTM D790
	3000 - 4000	psi	

KYNAR FLEX[®]

2850 PC

Compressive Strength, 73 °F	41.4 - 586	MPa	ASTM D695
	6000 - 85000	psi	
Unnotched Impact Strength, 73 °F	No Break	kJ/m	ASTM D256
Notched Impact Strength, 73 °F	0.16 - 0.427	kJ/m	ASTM D256
	3 - 8	ftlb/in	
Coefficient of Friction, Static vs. Steel, 73 °F	0.26	-	ASTM D1894
Coefficient of Friction, Dynamic vs. Steel, 73 °F	0.19	-	ASTM D1894
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	158	°C	ISO 11357-1/-3
Melting Point, 73 °F	155 - 160	°C	ASTM D3418
Glass Transition Temperature (Tg)	-40.6 - -38.3	°C	ASTM D7028
	-41 - -37	°F	
Temperature Rating	140	°C	UL RTI
	284	°F	
Temp. of Deflection Under Load, 1.80 MPa	46	°C	ISO 75-1/-2
	115	°F	
Heat Deflection Temperature, 264 Psi, 248 °F/hr	37.8 - 55	°C	ASTM D648
	100 - 131	°F	
Heat Deflection Temperature, 66 Psi, 248 °F/hr	60 - 75	°C	ASTM D648
	140 - 167	°F	
Coefficient of Thermal Expansion, 73 °F	12.6 - 18.5	10E-5/°C	ASTM D696
	7 - 10.3	10E-5/°F	
Burning Behav. at Thickness h	V-0	class	IEC 60695-11-10
Thickness Tested	0.8	mm	-
	0.0315	in	
Oxygen Index	43	%	ISO 4589-1/-2
Limiting Oxygen Index, 73 °F	43	%	ASTM D2863
Thermal Conductivity	0.144 - 0.18	W/(m K)	ASTM D433
	1 - 1.25	BTU in /(hr ft2 F)	
Specific Heat	745 - 958	J/(kg K)	DSC
	0.28 - 0.36	BTU/(lb·°F)	
Thermal Decomposition TGA, in air	375	°C	1% wt. loss
	707	°F	
Thermal Decomposition TGA, in nitrogen	410	°C	1% wt. loss
	770	°F	

KYNAR FLEX[®]

2850 PC

ELECTRICAL PROPERTIES

Dielectric Constant, 1 kHz	3.5 - 10.2	-	ASTM D150
Dissipation Factor, 100 kHz	0.01 - 0.22	-	ASTM D150
Volume Resistivity	2E12	Ohm*m	IEC 60093
Volume Resistivity, DC 68 °F, 65% R.H.	2E14	Ohm*cm	ASTM D257
Dielectric (Electric) Strength, 73°F	1.3 - 1.6	kV/mil	ASTM D149

OTHER PROPERTIES

Water Absorption	0.03	%	Sim. to ISO 62
Density	1780	kg/m ³	ISO 1183
	1.78	g/cm ³	
Specific Gravity, 73 °F	1.77 - 1.8	-	ASTM D792

OPTICAL PROPERTIES

Refractive Index @ sodium D line	1.42	-	ASTM D542
----------------------------------	------	---	-----------