

KYNAR FLEX[®]

PPA 2200

Kynar Flex[®] resins are fluorinated thermoplastic copolymers.

Kynar Flex[®] PPA 2200 resin is specially designed pellet used as a polymer process aid (PPA) for polyolefins.

The use of Kynar Flex[®] PPA 2200 resin at 200 - 1000 ppm levels reduces extruder pressure, improves surface finish, reduces die build up, and improves gauge control.

PROPERTIES	VALUE	UNIT	TEST STANDARD
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	144	°C	ISO 11357-1/-3
OTHER PROPERTIES			
Density	700	kg/m ³	ISO 1183
	0.7	g/cm ³	
Bulk Density	0.6 - 0.8	g/cm ³	1% wt. loss

PROCESSING Film Extrusion, Sheet Extrusion, Other Extrusion	
DELIVERY FORM Granules	
REGIONAL AVAILABILITY North America, Europe, Asia Pacific, South and Central America, Near East/Africa	