

KYNAR FLEX®

PPA 5301

Kynar Flex® resins are fluorinated thermoplastic copolymers.

Kynar Flex® PPA 5300 resin is specially designed pellet used as a polymer process aid (PPA) for polyolefins.

The use of **Kynar Flex® PPA 5300 resin** at 200 - 1000 ppm levels reduces extruder pressure, improves surface finish, reduces die build up, and improves gauge control.

This product is also available on a powder form as **Kynar Flex® PPA 5301 resin**.

PROPERTIES	VALUE	UNIT	TEST STANDARD
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	165	°C	ISO 11357-1/-3
Melting Point, 73 °F	≤329	°C	ASTM D3418
OTHER PROPERTIES			
Density	700	kg/m³	ISO 1183
	0.7	g/cm³	
Bulk Density	0.5 - 0.9	g/cm³	1% wt. loss

PROCESSING

Film Extrusion, Sheet Extrusion, Other Extrusion

DELIVERY FORM

Powder

REGIONAL AVAILABILITY

North America, Europe, Asia Pacific, South and Central America, Near East/Africa